



Electrospinning and Additive Manufacturing: Adding Three-Dimensionality to Electrospun Scaffolds for Tissue Engineering

James A. Smith¹ and Elisa Mele^{2*}

¹Department of Neurosurgery, Medical University of Graz, Graz, Austria, ²Materials Department, Loughborough University, Loughborough, United Kingdom

OPEN ACCESS

Edited by:

Nihal Engin Vrana,
Sparta Medical, France

Reviewed by:

Paul Andrew Wieringa,
Maastricht University, Netherlands
Varvara Gribova,
Université de Strasbourg, France
Albana Ndreu Halili,
Aleksandër Moisiu University, Albania

*Correspondence:

Elisa Mele
e.mele2@lboro.ac.uk

Specialty section:

This article was submitted to
Biomaterials,
a section of the journal
Frontiers in Bioengineering and
Biotechnology

Received: 01 March 2021

Accepted: 16 November 2021

Published: 30 November 2021

Citation:


Smith JA and Mele E (2021)
Electrospinning and Additive
Manufacturing: Adding Three-
Dimensionality to Electrospun
Scaffolds for Tissue Engineering.
Front. Bioeng. Biotechnol. 9:674738.
doi: 10.3389/fbioe.2021.674738

The final biochemical and mechanical performance of an implant or scaffold are defined by its structure, as well as the raw materials and processing conditions used during its fabrication. Electrospinning and Additive Manufacturing (AM) are two contrasting processing technologies that have gained popularity amongst the fields of medical research i.e., tissue engineering, implant design, drug delivery. Electrospinning technology is favored for its ability to produce micro- to nanometer fibers from polymer solutions and melts, of which, the dimensions, alignment, porosity, and chemical composition are easily manipulatable to the desired application. AM, on the other hand, offers unrivalled levels of geometrical freedom, allowing highly complex components (i.e., patient-specific) to be built inexpensively within 24 hours. Hence, adopting both technologies together appears to be a progressive step in pursuit of scaffolds that better match the natural architecture of human tissues. Here, we present recent insights into the advances on hybrid scaffolds produced by combining electrospinning (melt electrospinning excluded) and AM, specifically multi-layered architectures consisting of alternating fibers and AM elements, and bioinks reinforced with fibers prior to AM. We discuss how cellular behavior (attachment, migration, and differentiation) is influenced by the co-existence of these micro- and nano-features.

Keywords: electrospinning, tissue engineering, additive manufacturing, hybrid scaffolds, nanofibers

INTRODUCTION

Electrospinning is a nanofabrication technique based on the use of high electric voltages to produce polymeric fibers with micro-to nanometer diameters and distinct morphological features (Xue et al., 2019; Jain et al., 2020). A typical electrospinning process consists in ejecting an electrified polymer jet from the tip of a spinneret by applying a voltage (more than tens of kV) between the spinneret and a conductive collector. The jet is usually a polymer solution or melt, while a metallic needle connected to a syringe is used as spinneret, and a plate, disk or cylinder can be used as metallic collector (Guzman-Puyol et al., 2016). The polymer jet stretches, decreases in diameter, and solidifies before reaching the collector, where a network of solid fibers is deposited. Modifications of the standard electrospinning set-up have been proposed over the years to achieve control over fibers' density, degree of alignment, porosity, chemical composition, and production rate. Examples include solution electrospinning, melt electrospinning,



multi-jet electrospinning, needleless electrospinning, coaxial electrospinning, and near-field electrospinning (dos Santos et al., 2020).

The biomedical sector particularly benefits from electrospinning for the development of advanced systems that are relevant to tissue engineering and drug delivery (Mele, 2016; Denchai et al., 2018; Rahmati et al., 2020). One main advantage offered by this technique is flexible material selection, as a variety of biocompatible and/or biodegradable materials can easily be processed, including synthetic polymers, naturally derived polymers, and nanocomposites. In addition, the fibrous architecture generated promotes cellular activity by resembling the extracellular matrix (ECM) of native tissues. The high exposed nanofiber surface area (surface-to-volume ratio) aids in the encapsulation and release of bioactive compounds, within therapeutic limits. The high porosity control enables the mechanical performance of the fibrous mats to be tailored, in order to support cellular growth and promote the diffusion of nutrients/gases, and cell infiltration.

Strategies to further enhance the relevance of electrospun materials for tissue engineering applications have recently led to novel three-dimensional (3D) scaffolds with multi-scale hierarchical architectures (Moroni et al., 2008; Dalton et al., 2013; Balzamo et al., 2020; Chen et al., 2020a; Eom et al., 2020; Rahmati et al., 2020). These have been produced by combining electrospinning with techniques such as electro-spraying, gas foaming, phase separation, freeze-drying, additive manufacturing, leaching, and moulding.

This review focuses on recent advances in hybrid scaffold fabrication through the combination of electrospinning (melt electrospinning excluded) and additive manufacturing, and discusses how cellular behavior, such as attachment, migration, and differentiation, is influenced by the co-existence of micro- and nano-features.

COMBINATION OF ELECTROSPINNING AND ADDITIVE MANUFACTURING

In the literature, two main fabrication approaches that combine electrospinning and additive manufacturing have been reported so far to produce scaffolds for tissue engineering (Figure 1). These are: layer-by-layer deposition of electrospun nanofibers and 3D printed elements, referred to as multi-layered architectures; 3D printing of inks that contain electrospun nanofibers, indicated as composite inks. In addition, recent studies have explored the use of uniaxially aligned electrospun fibers to functionalise the surface of 3D printed struts to enhance cellular adhesion, proliferation and differentiation (Yeo and Kim, 2019; Yeo and Kim, 2020).

Multi-Layered Architectures

Depositing electrospun mats upon 3D printed substrates is one strategy used to develop multi-scale composite scaffolds (Moroni et al., 2008; Park et al., 2008; Mota et al., 2011; Yang et al., 2015; Naghieh et al., 2017; Rajzer et al., 2018; Yoon et al., 2019; Gao et al., 2020; Huang et al., 2020; Touré et al., 2020; Vyas et al., 2020; Yang et al., 2020; Yu et al., 2020). One seminal work proposed the manufacture of scaffolds consisting of alternating layers of randomly distributed electrospun nanofibers and 3D printed meshes (Moroni et al., 2008). It was demonstrated that these electrospun layers improved primary bovine articular chondrocyte entrapment within the scaffolds, stimulating extracellular matrix production for cartilage tissue formation. Additional research has further explored the co-existence of electrospun fibers (usually randomly distributed) and 3D printed elements within the same scaffold to influence cellular behavior (Mota et al., 2011; Yang et al., 2015). Multi-layer skin substitutes have been developed by depositing electrospun polycaprolactone (PCL) and keratin fibers on to the two surfaces of a PCL 3D printed scaffold (Choi et al., 2021), aiming at mimicking the histological structure of skin. The top




FIGURE 2 | (A) hADSCs seeding efficiency of the following types of 3D printed PCL scaffolds (4 h of incubation): without electrospun fibers (PCL); with electrospun fibers deposited at 0 rpm for 45 s (PLR); with electrospun fibers deposited at 0 rpm for 120 s (PHR); with electrospun fibers deposited at 1,000 rpm for 120 s (PL1000); with electrospun fibers deposited at 1,000 rpm for 360 s (PH1000). **(B)** Number of hADSCs detected on the five types of scaffolds at 4, 72 and 168 h of cell culture test. Scanning electron microscopy (SEM) images of **(C)** PCL scaffold, **(D)** PHR scaffold and **(E)** PH1000 scaffold after 1 day of cell culture. The SEM images show cells attached on the structures of the scaffolds and the alignment of the cytoskeleton when aligned nanofibers are present. Reprinted from (Huang et al., 2020).

electrospun layer (100 μm thick) consisted of nanofibers ($\sim 0.7 \mu\text{m}$ average diameter) to support the growth of human immortalized keratinocytes (HaCaT); while the bottom layer (300 μm thick) was made of microfibers ($\sim 1.7 \mu\text{m}$ average diameter) to enable the proliferation of normal human dermal fibroblasts (NHDF). HaCaT and NHDF cells were co-cultured onto the scaffolds for 4 days before *in-vivo* tests. Animal tests showed that the presence of keratin promoted wound closure, epithelialization, proliferation of both keratinocytes and fibroblasts, and collagen deposition at the wound site. In this work, fiber's diameter was effectively used to control cellular growth, and promote the formation of distinctive layers of keratinocytes and fibroblasts by stopping fibroblasts to infiltrate the nanofibrous layer.

In another study, a rotating drum electrospinning system was adopted to control the density (fibers per unit area) and the degree of alignment of electrospun fibers (Huang et al., 2020). Furthermore, similar systems have been combined with screw-assisted extrusion-based additive manufacturing to produce

porous PCL scaffolds for bone tissue engineering (Huang et al., 2020). PCL was firstly 3D printed ($0^\circ/90^\circ$ lay down pattern, 350 μm square pores) and the resulting 3D printed element was fixed on the electrospinning collector, which was rotated at different speeds. The presence of these PCL nanofibers promoted human adipose-derived stem cell (hADSCs) attachment and influenced their osteogenic differentiation. High density electrospun mats exhibited higher cell seeding efficiencies ($\sim 80\%$) compared to scaffolds with ($\sim 50\%$) and without ($\sim 30\%$) aligned nanofibers. Reductions in cell seeding efficiencies were attributed to the low porosity of the scaffolds, limiting cellular infiltration (Figure 2). The surface topography of the hybrid scaffolds greatly affected the behavior of hADSCs and aligned fibers acted as physical cues for mechano-transduction. Elongation and stretching of the cellular cytoskeleton along the direction of the fibers was observed when the hADSCs were seeded onto scaffolds with highly aligned electrospun fibers.

Recently, complex scaffolds have been manufactured to treat intervertebral disc (IVD) degeneration (Zhu et al., 2021). They

were composed of three main elements: a 3D printed frame of poly (lactic acid) (PLA) to simulate the IVD structure; bundles of oriented porous nanofibres of poly (L-lactide)/octa-armed polyhedral oligomeric silsesquioxanes (PLLA/POSS-(PLLA)₈) to mimic the annulus fibrosus (AF) structure; a gellan gum/poly (ethylene glycol) diacrylate (GG/PEGDA) double network hydrogel that encapsulated living bone marrow mesenchymal stem cells (BMSCs) to reproduce the nucleus pulposus (NP) structure. 3D printing offered great control over size and shape of the scaffolds that were tested in an animal model of IVD replacement at rat tail vertebra. The tests revealed that, after 6 months of implantation, the artificial scaffolds were effective as reimplanted autologous discs in terms of maintained disc height and production of new ECM (proteoglycans and collagen). This work demonstrates the potential of the hybrid technology (3D printing and electrospinning) for the manufacturing of personalized medical devices for IVD regeneration.

Electrospun layers can be used not only as biomimetic interface to direct cellular attachment and migration, but also as mechanical reinforcement elements, particularly when hydrogels are 3D printed (instead of thermoplastic polymers). For example, PCL electrospun mats were combined with alginate hydrogel (3D bioprinting) to create multi-layered hybrid constructs (Yoon et al., 2019).

Alginate-PCL scaffolds recorded a 4-fold increase in compressive tangential modulus (~ 89 kPa with nanofibers and ~ 23 kPa without nanofibers) at 30% strain. Furthermore, alginate-PCL scaffolds witnessed elastic recovery (without failure) up to a strain limit of 45% vs. 30% for specimens constructs without fibers. These results were credited to the elastic nature of PCL, which improved the resilience of the scaffolds. In addition, the nanofibrous layers increased the proliferation rate of NIH 3T3 fibroblasts (1.8-fold increase compared to constructs without fibers) by offering favorable perfusion conditions i.e., open porosity throughout their scaffold structure.

Electrospun nanofiber interleaves have been proposed to improve the mechanical properties of PLA 3D printed structures (He and Molnár, 2021). The nanofibrous mats were incorporated between 3D printed layers following a multi-step process. The first step was to electrospin PLA onto an aluminium foil by controlling the process time to achieve mats with the desired density/thickness. The first 3D printed layer was then deposited onto one surface of the electrospun mat. Interfacial bonding between the printed struts and the nanofibres was achieved by controlling the printing parameters and specifically the nozzle temperature ($\sim 220^\circ\text{C}$) that reduced the viscosity of the polymer melt and facilitated adhesion. After peeling off the aluminium foil, the composite was turned upside down and a second layer was printed on the other surface of the electrospun mat. The mechanical properties of the produced 3D printed composites with nanofiber interleaves were tested in tension. It was observed a 34.3% increase in Young's modulus for composites with a nanofiber content of 10.1 wt% if compared with neat PLA. Increases in tensile strength and elongation were also detected when 6.5 wt% and 10.1 wt% of fibres were used, indicating that the nanofibrous mats were effective in connecting adjacent printed layers and toughen the composites.

Through the combination of electrospinning techniques and flexible material selection, naturally derived polymer scaffolds that can release bioactive compounds to promote soft tissue engineering, such as cartilage regeneration, have been explored. For example, fused filament fabrication (FFF) technologies were used to manufacture poly l-lactic acid (PLLA) scaffolds, prior to the deposition of electrospun gelatine and osteogenon (ossein-hydroxyapatite complex containing osteocalcin and type I collagen) nanofibers onto a single scaffold surface (Rajzer et al., 2018). Although the gelatine fibers were crosslinked with vapors of glutaraldehyde to improve their stability in aqueous solutions, the fibrous network was lost during mineralisation tests in simulated body fluid (SBF) (fusion between fibers occurred and a gel-like layer formed). After 7 days in SBF, the gelatine layer was covered by apatite crystals due to osteogenon mineralisation. In addition, *in vitro* cytotoxicity tests showed that murine fibroblasts L929 attached and proliferated onto the gelatine layer, indicating that the composite scaffolds were biocompatible.

Literature suggests that introducing electrospun nano-fibers into multi-layered scaffolds (produced by combination of electrospinning and 3D printing) has the ability to manipulate both the porosity and mechanical performance of the 3D printed constructs, as well as modulate cellular behavior (elongation and differentiation) through their intrinsic topological features. Structures made of various biocompatible and biodegradable polymers (synthetic and naturally derived) can be easily embedded within the same scaffold to obtain the desired functionality. Moreover, cell infiltration and proliferation within the scaffold can be promoted by altering density and thickness of electrospun fibrous membranes. So far, biodegradable aliphatic polyesters (PCL, PLA and PLA-based) have been primarily used for the 3D printing process, because they have a relatively low melting point, are generally inexpensive and widely available, and do not need post-processing to be crosslinked (Moetazedian et al., 2021). These polymers, however, are hydrophobic and can limit cell attachment. Future research could focus on replacing PCL and PLA with more hydrophilic materials that contain bioactive compounds to promote cell growth (proteins, growth factors, ceramic nanoparticles).

Nanofiber-Reinforced Bio-Inks

The incorporation of electrospun nanofibers into hydrogels is discussed in the literature to create injectable composite systems that can stimulate, for example, the growth of nerve cells (Rivet et al., 2015; Omidinia-Anarkoli et al., 2017). However, so far, only a few works have reported on bio-inks that are both reinforced with electrospun nanofibers and suitable for 3D printing (Chen et al., 2019; Chen et al., 2020b). In the first paper published on this topic (inks based on electrospun nanofibers for additive manufacturing), a bio-ink containing gelatin/poly lactic-co-glycolic acid (PLGA) electrospun nanofibers was used for cartilage regeneration (Chen et al., 2019). The preparation of the composite bio-ink required multiple complex processing steps, such as the dehydration of the gelatin/PLGA mats, their homogenisation in a solvent (tert-butanol) to obtain short fibers, complete evaporation of the solvent, dispersion of the short

gelatin/PLGA fibers into a viscous water solution of hyaluronic acid and polyethylene oxide (PEO). Scaffolds were then 3D printed by extrusion, before freeze-drying and crosslinking to improve their mechanical stability. This fabrication procedure enabled the formation of scaffolds with interconnected multi-scale porosity due to the 3D printed strands and the electrospun fibrous network (whose structure was preserved). In compression, gelatin/PLGA fibers determined an increase in the Young's modulus, with scaffolds reporting values of ~ 600 kPa; while 3D printed scaffolds containing gelatin/PLGA powder (no fibers) were characterised by Young's modulus of ~ 100 kPa. The ability of the 3D printed scaffolds to regenerate cartilage tissue was investigated *in vitro* with chondrocytes and *in vivo* on mice. After 6 weeks of cell culture, chondrocytes produced ECM to cover the 3D scaffolds and cartilage-like tissue was formed. Similarly, 8 weeks after animal implantation, cartilage tissue with the structure and composition to the native tissue was generated (DNA and collagen content, and Young's modulus). These results were attributed to the porosity of the scaffolds, that allowed uniform cells infiltration and nutrients diffusion.

In follow-up studies, the bioactivity of such composite bio-inks and their regenerative potential were further enhanced by adding cartilage decellularized matrix (CDM) (Chen et al., 2020b). CDM particles were obtained from cow scapular cartilage after acellularization, freeze drying and pulverisation. They were dispersed in a hyaluronic acid solution together with gelatin/PLGA nanofibers and scaffolds were 3D printed as previously described. Articular cartilage regeneration in rabbits was observed after 12 weeks of implantation with significant deposition of collagen type II; while scaffolds without CDM showed a partially filled defect with limited collagen deposition.

The literature here discussed shows that the inclusion of electrospun nanofibers in bio-inks for additive manufacturing is an approach far more complex and time-consuming than the multi-layering methods described in *Multi-Layered Architectures* Section, because it requires additional dehydration, freeze-drying and cross-linking procedures. Nevertheless, it offers advantages in terms of obtaining scaffolds with enhanced porosity, controlled mechanical properties, and improved cellular viability. This is in line with previous research on the 3D bioprinting of hydrogels reinforced with polymeric nanofibers but not electrospun ones, including inks containing PLA nanofibers (produced by extrusion) (Narayanan et al., 2016; Kosik-Kozioł et al., 2017), and silk fibroin fibers (produced by mechanical grinding of degummed silkworm silk fibers) (Sakai et al., 2020).

FUTURE OUTLOOK

The need to create functional and structurally complex scaffolds for tissue engineering has motivated the research of novel

manufacturing methods that operate across different length scales. One strategy that has shown potential is the combination of electrospinning and 3D printing to enable, as discussed in this review, the production of scaffolds with multiscale porosity and hierarchical architecture. The presence of electrospun nanofibers and 3D printed micro-features within the same scaffold provides morphological and biomechanical cues that can regulate cellular behavior and promote tissue regeneration. Although a promising approach, combining these two techniques is currently time consuming and limited to research laboratories, because two separate set-ups, namely one for electrospinning and one for 3D printing, are typically required. In addition, post-processing procedures, such as freeze drying and/or crosslinking, are used to stabilise the complex structures created. Future works could focus on developing high-throughput automated systems, which integrate electrospinning and 3D printing (Mendoza-Buenrostro and Rodriguez, 2015), to achieve further control over the deposition of the nanofibers (density, thickness, and alignment degree) and increase the production rate of hybrid scaffolds.

In a recent work, a 3D printer was specifically modified to include electrospinning units (within its construct), for vascular tissue engineering applications (Fazal et al., 2021). The hybrid system can produce layered structures formed of electrospun mats and hydrogel, because it consists of one bioprinting head and two electrospinning heads (for co-electrospinning). Preliminary tests have demonstrated the fabrication of hollow tubular constructs. Gelatin methacrylate was first 3D printed around a rotating needle and photo-crosslinked; subsequently, electrospun fibers of PCL, polyvinylpyrrolidone (PVP) or polyethylene glycol (PEG) were deposited onto the external surfaces of the gelatine tubes.

The inclusion of multiple-electrospinning units within the confines of the hybrid technology could enable the fabrication and precise placement of nanofibers, constructed from different materials. This could promote localized cell-specific differentiation from Mesenchymal Stem Cells (MSCs) within the scaffold, leading to the generation of highly tunable interconnected multi-cellular/tissue systems. Such scaffolds could be used to develop sophisticated tissue models, better resembling natural tissue architectures, for future drug delivery and tissue replacement therapies. Alongside such prospects, protocols surrounding best practice e.g., sterilization methods for multi-cellular scaffolds would need to be investigated prior to implantation.

AUTHOR CONTRIBUTIONS

EM conceived the manuscript. JS and EM wrote the manuscript.

REFERENCES

- Balzamo, G., Zhang, X., Bosbach, W. A., and Mele, E. (2020). *In-situ* Formation of Polyvinylidene Fluoride Microspheres within Polycaprolactone Electrospun Mats. *Polymer* 186, 122087. doi:10.1016/j.polymer.2019.122087
- Chen, S., John, J. V., McCarthy, A., and Xie, J. (2020a). New Forms of Electrospun Nanofiber Materials for Biomedical Applications. *J. Mater. Chem. B* 8, 3733–3746. doi:10.1039/D0TB00271B
- Chen, W., Xu, Y., Li, Y., Jia, L., Mo, X., Jiang, G., et al. (2020b). 3D Printing Electrospinning Fiber-Reinforced Decellularized Extracellular Matrix for Cartilage Regeneration. *Chem. Eng. J.* 382, 122986. doi:10.1016/j.cej.2019.122986
- Chen, W., Xu, Y., Liu, Y., Wang, Z., Li, Y., Jiang, G., et al. (2019). Three-dimensional Printed Electrospun Fiber-Based Scaffold for Cartilage Regeneration. *Mater. Des.* 179, 107886. doi:10.1016/j.matdes.2019.107886
- Choi, W. S., Kim, J. H., Ahn, C. B., Lee, J. H., Kim, Y. J., Son, K. H., et al. (2021). Development of a Multi-Layer Skin Substitute Using Human Hair Keratinic Extract-Based Hybrid 3D Printing. *Polymers* 13, 2584. doi:10.3390/polym13162584
- Dalton, P. D., Vaquette, C., Farrugia, B. L., Dargaville, T. R., Brown, T. D., and Huttmacher, D. W. (2013). Electrospinning and Additive Manufacturing: Converging Technologies. *Biomater. Sci.* 1, 171–185. doi:10.1039/C2BM00039C
- Denchai, A., Tartarini, D., and Mele, E. (2018). Cellular Response to Surface Morphology: Electrospinning and Computational Modeling. *Front. Bioeng. Biotechnol.* 6, 155. doi:10.3389/fbioe.2018.00155
- dos Santos, D. M., Correa, D. S., Medeiros, E. S., Oliveira, J. E., and Mattoso, L. H. C. (2020). Advances in Functional Polymer Nanofibers: from Spinning Fabrication Techniques to Recent Biomedical Applications. *ACS Appl. Mater. Inter.* 12, 45673–45701. doi:10.1021/acsami.0c12410
- Eom, S., Park, S. M., Hong, H., Kwon, J., Oh, S.-R., Kim, J., et al. (2020). Hydrogel-assisted Electrospinning for Fabrication of a 3D Complex Tailored Nanofiber Macrostructure. *ACS Appl. Mater. Inter.* 12, 51212–51224. doi:10.1021/acsami.0c14438
- Fazal, F., Diaz Sanchez, F. J., Waqas, M., Koutsos, V., Callanan, A., and Radacsi, N. (2021). A Modified 3D Printer as a Hybrid Bioprinting-Electrospinning System for Use in Vascular Tissue Engineering Applications. *Med. Eng. Phys.* 94, 52–60. doi:10.1016/j.medengphy.2021.06.005
- Gao, D., Wang, Z., Wu, Z., Guo, M., Wang, Y., Gao, Z., et al. (2020). 3D-printing of Solvent Exchange Deposition Modeling (SEDM) for a Bilayered Flexible Skin Substitute of Poly (Lactide-co-glycolide) with Bioorthogonally Engineered EGF. *Mater. Sci. Eng. C* 112, 110942. doi:10.1016/j.msec.2020.110942
- Guzman-Puyol, S., Heredia-Guerrero, J. A., Ceseracciu, L., Hajiali, H., Canale, C., Scarpellini, A., et al. (2016). Low-cost and Effective Fabrication of Biocompatible Nanofibers from Silk and Cellulose-Rich Materials. *ACS Biomater. Sci. Eng.* 2, 526–534. doi:10.1021/acsbiomaterials.5b00500
- He, H., and Molnár, K. (2021). Fabrication of 3D Printed Nanocomposites with Electrospun Nanofiber Interleaves. *Additive Manufacturing* 46, 102030. doi:10.1016/j.addma.2021.102030
- Huang, B., Aslan, E., Jiang, Z., Daskalakis, E., Jiao, M., Aldalbah, A., et al. (2020). Engineered Dual-Scale Poly (ϵ -Caprolactone) Scaffolds Using 3D Printing and Rotational Electrospinning for Bone Tissue Regeneration. *Additive Manufacturing* 36, 101452. doi:10.1016/j.addma.2020.101452
- Jain, R., Shetty, S., and Yadav, K. S. (2020). Unfolding the Electrospinning Potential of Biopolymers for Preparation of Nanofibers. *J. Drug Deliv. Sci. Technology* 57, 101604. doi:10.1016/j.jddst.2020.101604
- Kosik-Kozioł, A., Costantini, M., Bolek, T., Szöke, K., Barbetta, A., Brinckmann, J., et al. (2017). PLA Short Sub-micron Fiber Reinforcement of 3D Bioprinted Alginate Constructs for Cartilage Regeneration. *Biofabrication* 9, 044105. doi:10.1088/1758-5090/aa90d7
- Mele, E. (2016). Electrospinning of Natural Polymers for Advanced Wound Care: towards Responsive and Adaptive Dressings. *J. Mater. Chem. B* 4, 4801–4812. doi:10.1039/C6TB00804F
- Mendoza-Buenrostro, C., Lara, H., and Rodriguez, C. (2015). Hybrid Fabrication of a 3D Printed Geometry Embedded with PCL Nanofibers for Tissue Engineering Applications. *Proced. Eng.* 110, 128–134. doi:10.1016/j.proeng.2015.07.020
- Moetazedian, A., Gleadall, A., Han, X., Ekinci, A., Mele, E., and Silberschmidt, V. (2021). Mechanical Performance of 3D Printed Polylactide during Degradation. *Additive Manufacturing* 38, 101764. doi:10.1016/j.addma.2020.101764
- Moroni, L., Schotel, R., Hamann, D., de Wijn, J. R., and van Blitterswijk, C. A. (2008). 3D Fiber-Deposited Electrospun Integrated Scaffolds Enhance Cartilage Tissue Formation. *Adv. Funct. Mater.* 18, 53–60. doi:10.1002/adfm.200601158
- Mota, C., Puppi, D., Dinucci, D., Errico, C., Bártolo, P., and Chiellini, F. (2011). Dual-Scale Polymeric Constructs as Scaffolds for Tissue Engineering. *Materials* 4, 527–542. doi:10.3390/ma4030527
- Naghieh, S., Foroozmehr, E., Badrossamay, M., and Kharaziha, M. (2017). Combinational Processing of 3D Printing and Electrospinning of Hierarchical Poly(lactic Acid)/gelatin-Forsterite Scaffolds as a Biocomposite: Mechanical and Biological Assessment. *Mater. Des.* 133, 128–135. doi:10.1016/j.matdes.2017.07.051
- Narayanan, L. K., Huebner, P., Fisher, M. B., Spang, J. T., Starly, B., and Shirwaiker, R. A. (2016). 3D-Bioprinting of Polylactic Acid (PLA) Nanofiber-Alginate Hydrogel Bioink Containing Human Adipose-Derived Stem Cells. *ACS Biomater. Sci. Eng.* 2, 1732–1742. doi:10.1021/acsbiomaterials.6b00196
- Omidinia-Anarkoli, A., Boesveld, S., Tuvshindorj, U., Rose, J. C., Haraszti, T., and De Laporte, L. (2017). An Injectable Hybrid Hydrogel with Oriented Short Fibers Induces Unidirectional Growth of Functional Nerve Cells. *Small* 13, 1702207. doi:10.1002/sml.201702207
- Park, S. H., Kim, T. G., Kim, H. C., Yang, D.-Y., and Park, T. G. (2008). Development of Dual Scale Scaffolds via Direct Polymer Melt Deposition and Electrospinning for Applications in Tissue Regeneration. *Acta Biomater.* 4, 1198–1207. doi:10.1016/j.actbio.2008.03.019
- Rahmati, M., Mills, D. K., Urbanska, A. M., Saeb, M. R., Venugopal, J. R., Ramakrishna, S., et al. (2021). Electrospinning for Tissue Engineering Applications. *Prog. Mater. Sci.* 117, 100721. doi:10.1016/j.pmatsci.2020.100721
- Rajzer, I., Kurowska, A., Jabłoński, A., Jatteau, S., Śliwka, M., Ziłbka, M., et al. (2018). Layered Gelatin/PLLA Scaffolds Fabricated by Electrospinning and 3D Printing- for Nasal Cartilages and Subchondral Bone Reconstruction. *Mater. Des.* 155, 297–306. doi:10.1016/j.matdes.2018.06.012
- Rivet, C. J., Zhou, K., Gilbert, R. J., Finkelstein, D. I., and Forsythe, J. S. (2015). Cell Infiltration into a 3D Electrospun Fiber and Hydrogel Hybrid Scaffold Implanted in the Brain. *Biomatter* 5, e1005527. doi:10.1080/21592535.2015.1005527
- Sakai, S., Yoshii, A., Sakurai, S., Horii, K., and Nagasuna, O. (2020). Silk Fibroin Nanofibers: a Promising Ink Additive for Extrusion Three-Dimensional Bioprinting. *Mater. Today Bio* 8, 100078. doi:10.1016/j.mtbio.2020.100078
- Touré, A. B. R., Mele, E., and Christie, J. K. (2020). Multi-layer Scaffolds of Poly(caprolactone), Poly(glycerol Sebacate) and Bioactive Glasses Manufactured by Combined 3d Printing and Electrospinning. *Nanomaterials* 10, 626. doi:10.3390/nano10040626
- Vyas, C., Ates, G., Aslan, E., Hart, J., Huang, B., and Bartolo, P. (2020). Three-Dimensional Printing and Electrospinning Dual-Scale Polycaprolactone Scaffolds with Low-Density and Oriented Fibers to Promote Cell Alignment. *3D Printing and Additive Manufacturing* 7, 105–113. doi:10.1089/3dp.2019.0091
- Xue, J., Wu, T., Dai, Y., and Xia, Y. (2019). Electrospinning and Electrospun Nanofibers: Methods, Materials, and Applications. *Chem. Rev.* 119, 5298–5415. doi:10.1021/acs.chemrev.8b00593
- Yang, G.-H., Kim, M., and Kim, G. (2015). A Hybrid PCL/collagen Scaffold Consisting of Solid Freeform-Fabricated Struts and EHD-Direct-Jet-Processed Fibrous Threads for Tissue Regeneration. *J. Colloid Interf. Sci.* 450, 159–167. doi:10.1016/j.jcis.2015.02.070
- Yang, Z., Song, Z., Nie, X., Guo, K., and Gu, Y. (2020). A Smart Scaffold Composed of Three-Dimensional Printing and Electrospinning Techniques and its Application in Rat Abdominal wall Defects. *Stem Cell Res Ther* 11, 533. doi:10.1186/s13287-020-02042-6
- Yeo, M., and Kim, G. (2020). Micro/nano-hierarchical Scaffold Fabricated Using a Cell electrospinning/3D Printing Process for Co-culturing Myoblasts and HUVECs to Induce Myoblast Alignment and Differentiation. *Acta Biomater.* 107, 102–114. doi:10.1016/j.actbio.2020.02.042

- Yeo, M., and Kim, G. (2019). Nano/microscale Topographically Designed Alginate/PCL Scaffolds for Inducing Myoblast Alignment and Myogenic Differentiation. *Carbohydr. Polym.* 223, 115041. doi:10.1016/j.carbpol.2019.115041
- Yoon, Y., Kim, C. H., Lee, J. E., Yoon, J., Lee, N. K., Kim, T. H., et al. (2019). 3D Bioprinted Complex Constructs Reinforced by Hybrid Multilayers of Electrospun Nanofiber Sheets. *Biofabrication* 11, 025015. doi:10.1088/1758-5090/ab08c2
- Yu, Y., Hua, S., Yang, M., Fu, Z., Teng, S., Niu, K., et al. (2020). Fabrication and Characterization of electrospinning/3D Printing Bone Tissue Engineering Scaffold. *RSC Adv.* 6, 110557–110565. doi:10.1039/c6ra17718b
- Zhu, M., Tan, J., Liu, L., Tian, J., Li, L., Luo, B., et al. (2021). Construction of Biomimetic Artificial Intervertebral Disc Scaffold via 3D Printing and Electrospinning. *Mater. Sci. Eng. C* 128, 112310. doi:10.1016/j.msec.2021.112310

Conflict of Interest: The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

Publisher's Note: All claims expressed in this article are solely those of the authors and do not necessarily represent those of their affiliated organizations, or those of the publisher, the editors and the reviewers. Any product that may be evaluated in this article, or claim that may be made by its manufacturer, is not guaranteed or endorsed by the publisher.

Copyright © 2021 Smith and Mele. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) and the copyright owner(s) are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.