



Bacteriogenic Platinum Nanoparticles for Application in Nanomedicine

Khalida Bloch¹, Karishma Pardesi², Cristina Satriano³ and Sougata Ghosh^{1,4*}

¹Department of Microbiology, School of Science, RK University, Rajkot, India, ²Department of Microbiology, Savitribai Phule Pune University, Pune, India, ³Department of Chemical Sciences, University of Catania, Catania, Italy, ⁴Department of Chemical Engineering, Northeastern University, Boston, MA, United States

Nanoscale materials have recently gained wide attention due to their potential to revolutionize many technologies and industrial sectors, including information technology, homeland security, transportation, energy, food safety, environmental science, catalysis, photonics and medicine. Among various nanoparticles, platinum nanoparticles (PtNPs) are widely used for biomedical applications, including imaging, implants, photothermal therapy and drug delivery. Indeed, PtNPs possesses intrinsic antimicrobial, antioxidant, and anticancer properties. Also, due to their remarkable catalytic activity, they are able to reduce the intracellular reactive oxygen species (ROS) levels and impair the downstream pathways leading to inflammation. Various approaches, including both physical and chemical methods, are currently employed for synthesis of PtNPs. However, the use of hazardous reaction conditions and toxic chemicals in these processes poses a potential threat to the environment and severely compromise the biocompatibility of the nanoparticles. Hereby, increasing need for exploitation of novel routes for synthesis of PtNPs has led to development of biological fabrication using microbes, specifically bacteria. Herein, we present a most comprehensive report on biogenesis of PtNPs by several bacteria like *Acinetobacter calcoaceticus*, *Desulfovibrio alaskensis*, *Escherichia coli*, *Shewanella algae*, *Plectonema boryanum*, etc. An overview of the underlying mechanisms of both enzymatic and non-enzymatic methods of synthesis is included. Moreover, this review highlights the scope of developing optimized process to control the physicochemical properties, such as the nanoparticle surface chemistry, charge, size and shape, which, in turn, may affect their nanotoxicity and response at the biointerface for nanomedicine applications.

Keywords: platinum nanoparticles, bacteriogenic synthesis, biointerfaces, surface characterization, nanomedicine

INTRODUCTION

Biological synthesis of nanoparticles has emerged as a promising area of nanobiotechnology which has attempted to develop environmentally benign green routes for synthesis of various nanostructures with exotic shape and sizes (Thakkar et al., 2010). Viruses, bacteria, fungi, algae and plants have been explored for their potential to synthesize gold, silver, copper, platinum, palladium, zinc and even magnetic nanoparticles (Ghosh and Webster, 2020a).

Among various metal nanoparticles platinum nanoparticles (PtNPs) are of great relevance and promising potentiality, owing to their multivariate applications in fuel cells, water gas shift reactions,

OPEN ACCESS

Edited by:

Jie He,
University of Connecticut,
United States

Reviewed by:

Lei Wang,
Harbin Institute of Technology, China
Ben Liu,
Sichuan University, China

*Correspondence:

Sougata Ghosh
ghoshsibb@gmail.com

Specialty section:

This article was submitted to
Nanoscience,
a section of the journal
Frontiers in Chemistry

Received: 31 October 2020

Accepted: 12 January 2021

Published: 05 March 2021

Citation:

Bloch K, Pardesi K, Satriano C and
Ghosh S (2021) Bacteriogenic
Platinum Nanoparticles for Application
in Nanomedicine.
Front. Chem. 9:624344.
doi: 10.3389/fchem.2021.624344

electronics, petrochemical industries, organic catalysis, selective oxidation of CO, automobiles, photonics, optics, biosensors and pharmaceuticals (Jeyaraj et al., 2019).

Various physical methods, such as vapour deposition, flame pyrolysis, laser ablation, sputter deposition, arc discharge, melt mixing and ball milling are used to synthesize monodispersed PtNPs. These physical methods consume enormous energy and dissipate radiations (Stepanov et al., 2014). Similarly, chemical methods for synthesis of PtNPs include the sol-gel process, plasma-enhanced chemical vapour deposition, pyrolysis, microemulsion, hydrothermal and polyol synthesis. These chemical methods involve toxic and hazardous chemicals for reduction of the metal ions to corresponding nanoparticles as well as for their stabilization (Ghosh et al., 2015). Therefore, there is need for developing clean, biocompatible, non-toxic, eco-friendly rapid and efficient methods for synthesis of PtNPs. We have reported fabrication of PtNPs and its alloy with palladium from medicinal plants like *Gloriosa superba*, *Barleria prionitis*, and *Dioscorea bulbifera*. Interestingly, biogenic PtNPs showed more anticancer activity compared to chemically synthesized nanoparticles (Ghosh et al., 2015; Rokade et al., 2017; Rokade et al., 2018). Fungi like *Fusarium oxysporum* and *Neurospora crassa* are reported to synthesize PtNPs either intracellularly or extracellularly with spherical, hexagonal, pentagonal, circular, squares and rectangular shapes (Ghosh et al. 2020).

Another attractive bottom up approach for synthesis of PtNPs that have attracted wide attention is bacteria mediated fabrication. Bacteria possess remarkable ability to reduce metal ions to corresponding nanoparticles which are highly stable with notable therapeutic properties. Hence, a wide number of bacterial species like *Acetobacter xylinum*, *Acinetobacter calcoaceticus*, *Desulfovibrio alaskensis*, *Escherichia coli*, *Shewanella algae*, *Plectonema boryanum*, and so forth are reported for synthesis of PtNPs with different shapes, sizes and biological activity (Gahlawat and Choudhury, 2019; Ghosh and Webster, 2020b). The synthesis of nanoparticles achieved by biogenic enzymatic process are excellent as compared to other methods. The NPs produced by this method showed greater catalytic potential. Microorganism adapt different environmental conditions and they produce NPs in order to generate energy and detoxify the toxic molecules to survive in adverse environments.

In this review an elaborate account of advances in the area of bacteriogenic synthesis of PtNPs is presented. Further, we have presented the mechanism of synthesis and the applications of bacteriogenic PtNPs. Finally, the limitations of microbial synthesis and the scope to overcome them are also discussed.

Synthesis, Advantages and Disadvantages

Various methods are used for the synthesis of PtNPs, which are broadly divided into two major categories: top-down and bottom-up approaches. In top-down approaches, metal in bulk amount is used for the synthesis of nanoparticles via mechanical breakdown (Dhand et al., 2015). The major advantage is uniform size and shape of resulting PtNPs. Several physical methods are used for the synthesis of PtNPs such as lithography, thermal decomposition, chemical etching and sputtering (Mafune and Kondow, 2004; Park et al., 2010; Cueto et al., 2011). In bottom-up

approach atoms and molecules assemble to generate range of NPs (Nichols et al., 2006). Sol-gel processing, laser pyrolysis, chemical vapour deposition and plasma spraying synthesis are included in bottom up approach. Synthesis methods are divided into three groups- physical, chemical and biological as depicted in **Figure 1**. The physical method involves high mechanical pressure, energy, and include evaporation and condensation to generate PtNPs. **Table 1** shows the advantages of physical method that include no use of toxic chemicals, purity, uniform size and shape whereas its disadvantage includes high cost, exposure to radiation, high temperature and less productivity. It also changes the physicochemical property of nanoparticles.

On the other hand chemical synthesis of PtNPs involves interaction of atoms and smaller molecules where the precursor metal ions are converted to corresponding nanoparticles. Water soluble precursors are used to enhance the reduction of metal monomers. Various synthesis techniques include sol-gel process, microemulsion, hydrothermal, polyol synthesis and pyrolysis (Bonnemann and Richards, 2001; Liu et al., 2002; Kyung Tae et al., 2013). The chemical synthesis is cost effective, highly versatile, high yielding, controllable, thermally stable and less dispersed but it also includes low purity, use of toxic chemicals and hence hazardous to human beings and environment.

Biological synthesis has recently gained much attention for the synthesis of PtNPs. The advantage of green synthesis is that they are simple, facile, ecofriendly, non toxic and biocompatible (Naseer et al. 2020). PtNPs with definite shape and size can be produced by changing the concentration of reducing agent, temperature and pH. The synthesis of PtNPs is limited as compared to synthesis of silver, gold and other metal NPs. Biological systems such as bacteria, fungi and plants are considered the potentially environment friendly nanofactories. Green synthesis are alternatives to physical and chemical methods as they are non toxic, cost effective, gives rapid synthesis, ecofriendly, monodispersed, low in waste production and also give large scale production (Jeyaraj et al., 2019).

BACTERIOGENIC PLATINUM NANOPARTICLES

Several bacteria have the ability to biosorb metal ions on their surface and eventually reduce them to the corresponding nanoparticles by various mechanisms that may include reductases, cytochromes and metallothioneins (Patel and Ponnuchamy, 2019; Gautam et al. 2020). Bacterial cellulose, rhizospheric bacteria, anaerobic sulphate reducing bacteria and even photoautotrophic cyanobacteria can synthesize PtNPs with exotic shape and size as presented in **Table 2**. In the following section bacteria with potential to synthesize PtNPs are discussed in details.

Acetobacter xylinum

Synthesis of platinum nanoparticles (PtNPs) was achieved using bacterial cellulose (BC) matrix of *A. xylinum*. Dry BC membrane was used for the synthesis of PtNPs where initially BC membrane was allowed to soak with different concentration of aqueous K_2PtCl_4 solution for 2 h followed by sonication at room




TABLE 1 | Advantages and disadvantages of different methods used for synthesis of PtNPs.

Methods	Advantage	Disadvantage
Physical method	High speed, no use of toxic chemicals, purity, uniform size and shape.	Productivity, high cost, exposure to radiation, require high energy, temperature and pressure, large amount of waste generation, high dilution, difficult size and shape tunability, lower stability, altered surface chemistry and physicochemical properties of nanoparticles.
Chemical method	Cost effective, high versatility in surface chemistry, easy functionalization, high yield, size controllability, thermal stability, reduced dispersity.	Low purity, use of toxic chemicals and organic solvents, hazardous to human beings and environment.
Bacteriogenic synthesis	Simple, facile ecofriendly, nontoxic and biocompatible.	Hard to control size, shape, crystal growth. Stability and aggregation, possible presence of endotoxin, time consuming purification processes.

temperature. Membrane was then washed with deionized water. Hydrogen gas was applied at 0.5 psi and stirred at 500 rpm for 1 h at room temperature to reduced Pt(II). Pt-BC gel was then dried and dry membrane composite was produced with thickness of 0.5–0.7 mm. The colour change of BC membrane from transparent white to black indicated deposition of Pt on the fibres of BC. White granules were found to be embedded on BC membrane which was revealed by SEM images. **Figure 2A** shows that the PtNPs varied in particle size ranging from 6.3–9.3 nm with varying salt concentration (Aritonang et al., 2014).

***Acinetobacter calcoaceticus* PUCM 1011**

A. calcoaceticus PUCM 1011, isolated from rhizosphere of *Pennisetum glaucum* was used for the synthesis of PtNPs. The bacteria were grown in Luria Bertani (LB) broth to obtain the cell pellet which was then suspended in sterile distilled water to get cell density 1 McFarland unit. Aqueous solution of hexachloroplatinic acid (H_2PtCl_6) was mixed with cell pellet to

get a final concentration of 1 mM. The resulting reaction mixture was allowed to incubate for 168 h at 30°C. The reaction mixture was held at different salt concentration (1–10 mM), pH (5–9) and temperature (20–50°C). Sharp absorption peak at 300 nm was displayed in the UV-Vis spectra of the bacteriogenic PtNPs. Intracellular cuboidal PtNPs of size ranging from 2–3.5 nm were synthesized. It was found that 1.07×10^{-3} mol/L of PtNPs were formed within 72 h at 30°C with 1 mM salt concentration. The PtNPs synthesized from purified bacterial cell proteins were in size ranging from 1–4 nm and also few were in picometer range (Gaidhani et al., 2014).

***Desulfovibrio alaskensis* G20**

Anaerobic sulfate reducing bacteria *D. alaskensis* G20 was used for the synthesis of PtNPs. The organism was grown on Postgate Media C (PGMC) where lactate was used as carbon source and was incubated in anaerobic hood fed with 10% CO_2 and H_2 at 30°C. The cell pellet was obtained by centrifuging the cells and was

TABLE 2 | Bacteria mediated synthesis of PtNPs.

Bacteria	Size	Shape	Localization	References
<i>Acetobacter xylinum</i>	6.3–9.3 nm	Granular	Extracellular and intracellular	Aritonang et al. (2014)
<i>Acinetobacter calcoaceticus</i> PUCM 1011	2–3.5 nm	Cuboidal	Intracellular	Gaidhani et al. (2014)
<i>Desulfovibrio alaskensis</i> G20	-	-	Extracellular	Capeness et al. (2015)
<i>Desulfovibrio vulgaris</i> Hildenborough (DSM 644)	-	-	Extracellular	Martins et al. (2016)
<i>Escherichia coli</i> MC4100	2.3 ± 0.7 nm and 4.5 ± 0.7 nm	Spherical	-	Attard et al. (2012)
<i>Plectonema boryanum</i> UTEX 485	30 nm–0.3 µm	Spherical	Intracellular and extracellular	Lengke et al. (2006)
<i>Calothrix pulvinata</i> ALCP 745A	3.2 ± 0.3	Well-shaped	Intracellular	Brayner et al. (2007)
<i>Anabaena flos-aquae</i> ALCP B24	-	-	Intracellular	Brayner et al. (2007)
<i>Leptolyngbya foveolarum</i> ALCP 671B	-	-	Intracellular	Brayner et al. (2007)
<i>Pseudomonas aeruginosa</i> SM1	450 nm	Circular disk like	Extracellular	Srivastava and Constanti, (2012)
<i>Shewanella algae</i>	5 nm	Discrete	Periplasmic	Konishi et al. (2007)
<i>Shewanella oneidensis</i> MR-1	3–40	Spherical	Intracellular and extracellular	Xu et al. (2019)
<i>Streptomyces</i> sp.	61.03	Snowflake shape	extracellular	Tuo et al. (2016)
<i>Sulphate reducing bacteria</i>	20–50 nm	Spherical	Extracellular	Baskaran et al. (2017)
	200–1000 nm	Irregular, rectangle and square	Cell free soluble extract	Riddin et al. (2010)
<i>Jeotgalicoccus coquinae</i> ZC15	5.74	Spherical	Extracellular	Eramabadi et al. (2020)
<i>Kocuria rosea</i> MN23	5.85	Spherical	Extracellular	Eramabadi et al. (2020)
<i>Pseudomonas kunmingensis</i> ADR19	3.95	Spherical	Extracellular	Eramabadi et al. (2020)
<i>Pseudomonas putida</i> KT2440	8.06	Spherical	Extracellular	Eramabadi et al. (2020)
<i>Psychrobacter faecalis</i> FZC6	2.49	Spherical	Extracellular	Eramabadi et al. (2020)
<i>Sporosarcina psychrophila</i> KC19	4.24	Spherical	Extracellular	Eramabadi et al. (2020)
<i>Vibrio fischeri</i> NRRL B-11177	3.84	Spherical	Extracellular	Eramabadi et al. (2020)





FIGURE 2 | Morphologies of bacteriogenic PtNPs. (A) SEM images of Pt-BCcm membrane obtained from K_2PtCl_4 solution at 10mM where inset scale bar represents 1 µm (Aritonang et al., 2014); (B) Representative electron micrographs of PtNPs produced by *D. alaskensis* G20 which are exported and found on the surface of the cell where inset scale bar represents 200 nm (Capeness et al., 2015); (C) TEM image of recovered bioPt NPs from 1% Pt EcMC4100 after NaOH, washing, and centrifugation treatment where inset scale bar represents 50 nm (Attard et al., 2012); TEM micrographs of partially recrystallized spherical PtNPs in cyanobacteria- $PtCl_4$ systems at (D) at 60°C and 14 days where inset scale bar represents 0.25 µm; (E) at 80°C and 21 days where inset scale bar represents 0.1 µm; (F) 100°C days and 28 days where inset scale bar represents 0.1 µm (Lengke et al., 2006).



suspended in 10 mM 3-(N-morpholino)-propanesulfonic acid (MOPS) buffer with pH 7. The 2 mM PtCl_4 salt was added to the cell suspension and was allowed to incubate for 2 h. **Figure 2B** depicts that the PtNPs were produced extracellularly and were adhered to the cell surface (Capeness et al., 2015).

Desulfovibrio vulgaris Hildenborough (DSM 644)

PtNPs were also biologically synthesized using *D. vulgaris* Hildenborough (DSM 644). Modified Postgate media C (pH 7.2) (0.5 g/L KH_2PO_4 , 1 g/L NH_4Cl , 2.5 g/L Na_2SO_4 , 0.06 g/L $\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$, 0.06 g/L $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$, 1 g/L yeast extract, 0.0071 g/L $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$, 0.3 g/L sodium citrate tribasic dihydrate, 0.1 g/L ascorbic acid, 0.1 g/L sodium thioglycolate, 4.5 g/L sodium lactate and 0.3 g/L resazurin) was used for the growth of organism. The cells were harvested by centrifugation and were washed with anaerobic MOPS/NaOH buffer (20 mM, pH 6.8). The cell suspension was added to metal salt solution (100 mg/L, pH 2.5) and the reaction mixture was kept under anaerobic condition. After 1 h of incubation under an atmosphere of hydrogen, the reaction mixture was kept overnight at 37°C under 0.8 bar pressure. Bioreduced PtNPs were deposited on the cell surface which confirmed extracellular mode of synthesis (Martins et al., 2016).

Escherichia coli MC4100

In another study *E. coli* MC4100 was grown aerobically on nutrient agar plate at 30°C while for catalyst preparation the bacteria were grown anaerobically in nutrient broth (NB) at 37°C (pH 7.3).

Bacterial culture was harvested under oxygen-free nitrogen (OFN) by centrifugation and was treated with degassed 20 mM Na-MOPS (3-(N-morpholino) propanesulfonic acid) buffer. Cell culture was then transferred anaerobically into serum bottle and mixed with degassed 2 mM of Na_2PtCl_4 to achieve the final ratio of 1:99 and 1:5 (weight of Pt: dry weight of cells). The reaction mixture was incubated for 30 min at 30°C to allow biosorption of Pt(II) on the cell surface followed by passage of hydrogen gas for 10 min at 20°C at pH 2.3 that led to reduction of Pt(II) to Pt(0). The bioreduced PtNPs were harvested by centrifugation and were kept for 6 weeks with 5.5 M NaOH for the removal of organic material coating. The PtNPs were then deposited on gold electrode for the electrochemical measurements. **Figure 2C** illustrates that the spherical PtNPs (with 1% by mass metal loading) were 2.3 ± 0.7 nm in diameter while spherical PtNPs generated with 20% metal loading exhibited an average size of 4.5 ± 0.7 nm (Attard et al., 2012).

Plectonema boryanum UTEX 485

PtNPs were synthesized employing cyanobacteria, *P. boryanum* UTEX 485 that was grown in batch culture using BG-11 medium buffered with 10 mM HEPES at 29°C in presence of CO_2 . The cyanobacteria were allowed to grow for 6–8 weeks and cells were harvested by centrifugation and then 5 ml of PtCl_4 (~500 mg/L) was added to 5 ml cyanobacterial culture. The reaction mixture was held at different temperature (25, 60, 80 and 100°C) for 28 days. The reaction was also allowed to incubate at 180°C for 1 day in order to check the effect of temperature on morphology. SEM analysis revealed that the shape of the particle (incubated at 25°C) was found to be spherical with size ranging from 30 nm to 0.3 μm . TEM-EDS showed the presence of platinum with sulfur,

iron and chloride. At 60 °C and 80 °C, particles were spherical with size 30 nm to 0.2 μm which formed long beadlike chains (Figures 2D,E). At 100 °C, very fine grained PtNPs were observed as seen in Figure 2F. However, at 180 °C PtNPs formed a branched pattern exhibiting a dendritic morphology. X-ray Photoelectron Spectroscopy (XPS) was carried out to investigate oxidation state of platinum and sulfur (Lengke et al., 2006).

Among several other cyanobacteria *Anabaena*, *Calothrix*, and *Leptolyngbya* were also used for the synthesis of PtNPs. *Calothrix pulvinata* ALCP 745A, *Anabaena flosaquae* ALCP B24, *Leptolyngbya foveolarum* ALCP 671B were cultivated in sterile Bold's Basal medium for different time periods like one month, 20 days and 6 days. *In-vitro* enzymatic reduction assay was carried out to confirm that nitrogenase is responsible for the reduction of PtNPs. Bold's Basal medium with nitrogenase enzyme as reducing agent was used along with *Calothrix* released polysaccharides (RPS) in order to simulate *in vivo* conditions. The size of PtNPs synthesized from *Calothrix* was found to be 3.2 ± 0.3 nm. The binding energy after peak decomposition were found to be 71.0, 73.4 and 75.8 eV for *Calothrix* and 71.5, 73.7 and 75.8 eV for *Anabaena* (Brayner et al., 2007).

***Pseudomonas aeruginosa* SM1**

P. aeruginosa SM1 was used for the extracellular synthesis of PtNPs where the organism was initially cultured in nutrient broth (10 g/L peptone, 10 g/L meat extract and 0.5 g/L NaCl) and was incubated at 27 °C under shaking condition (120 rpm). Then bacterial cell pellet (0.2 g) was added to 0.001 M of ammonium hexachloroplatinate (IV) ((NH₄)₂PtCl₆) solution and the reaction mixture was kept at 25 °C. Morphological analysis using TEM showed that the PtNPs were circular disk like with a size of 450 nm. The primary and secondary amines in the bacterial metabolites were reported to be responsible for the synthesis of extracellular PtNPs (Srivastava and Constanti, 2012).

Shewanella algae

S. algae ATCC 51181 was used for the biological synthesis of PtNPs where the bacterial strain was anaerobically cultured in ATCC medium 2 containing sodium lactate in presence of N₂-CO₂ (80:20, v/v). Cells were recovered by centrifugation and suspended in bicarbonate buffer. Cell suspension was added into 10 ml of aqueous H₂PtCl₂ solution to achieve a final cell concentration of 1×10^9 cells/ml and the reaction mixture was incubated at 25 °C. The colour change from pale yellow to black within 60 min indicated formation of discrete PtNPs which were 5 nm in size and were located in periplasmic space between inner and outer membrane of the bacterial cell (Konishi et al., 2007).

***S. oneidensis* MR-1**

Biogenic synthesis of PtNPs was checked using *S. oneidensis* MR-1 (ATCC 700550) in absence and presence of quinone. Mineral salt medium was inoculated with cell in which formate was used as electron donor and H₂PtCl₆ (H₂O)₆ salt as precursor for the synthesis of PtNPs. Reaction took place in dark anaerobically at 30 °C for 24 h that led to 100% reduction of metal salt to PtNPs that was indicated by the appearance of black colour. Small clusters of snowflake shaped PtNPs were observed on the

surface of the bacterial cell with size of 61.03 nm. Further, addition of Anthraquinone-2,6- disulfonate (AQDS) enhanced the reduction process resulting in smaller and larger PtNPs with 2.45 nm and 120 nm sizes, respectively (Tuo et al., 2016).

Green synthesis of Pd-Pt alloys NPs was reported using *S. oneidensis* MR-1 in presence of mixed solution of 100 mg/L of Pd (II) and Pt (IV). Sodium formate was added and the reaction mixture was allowed to incubate for 3 h at 30 °C resulting in synthesis of Pd-Pt NPs both intracellularly and extracellularly which were mostly spherical with 3–40 nm size. Also spherical extracellular nanoparticles with size of 12–40 nm were found to be located onto the surface of the cell with average size of 26.0 nm. Hence the extracellular particles were larger in size than the intracellular. The surface enzymes, proteins, reducing components of bacteria aided in reduction of metal ion. Amines, carbonyl and hydroxyl functional group of protein and polysaccharides might have played a critical role as reducing and stabilizing agent during biosynthesis of Pd-Pt alloys NPs (Xu et al., 2019).

***Streptomyces* sp.**

PtNPs were synthesized from *Streptomyces* sp. isolated from Kodiyakarai marine segment of Tamil Nadu, India. The biomass of *Streptomyces* sp. was recovered by centrifuging at 10,000 rpm followed by filtration through polyethersulphone filter to produce cell free supernatant (CFS). Different concentration of CFS was mixed with aqueous potassium hexachloroplatinate (IV) (K₂PtCl₆) solution (1 mM) and was incubated for 24 h at 30 °C. UV-Vis spectra showed absorption peak at 262 nm indicating synthesis of PtNPs which were face centered cubic (FCC) of crystalline nature with size of 24.1 nm. Atomic force microscopy (AFM) and TEM analyses confirmed that the size of the bacteriogenic PtNPs were spherical with 20–50 nm size (Baskaran et al., 2017).

Sulphate Reducing Bacteria (SRB)

SRB were isolated from sewage sludge obtained from Environmental Biotechnological Research Unit (EBRU) Bio-sure Process (Grahamstown, South Africa) was used for the synthesis of PtNPs. The organism was cultured under anaerobic conditions in dark at room temperature by exposing to N₂ (99.9%) and H₂ (99%) for 15 min and 5 min, respectively (Riddin et al., 2009). The SRB cells were harvested and pellet was washed with double distilled water to remove sulfide or sulfate. The cell-free soluble extract (CSE) was incubated on ice for 10 min and 250 μg/ml protein from CSE was mixed with H₂PtCl₆ such that the ratio of salt solution to protein varied from 0.7:1 to 4:1. The pH was adjusted to 9.0 and the reaction mixture was incubated in dark at 65 °C. The gradual color change from light yellow to brown indicated formation of PtNPs. Lower percentage of soluble protein resulted in slow reduction of platinum salt. TEM analysis revealed that 0.7:1 sample showed irregular, electron dense particles with 200–1000 nm size while sample with 1:1 ratio had particle size 100–500 nm with rectangles and squares shapes. Particle size of PtNPs were in range from 200–800 nm with irregular shape when the reactant ratio was 1.5:1 (Riddin et al., 2010).

Microbial Cell Lysate Supernatant (CLS)

In another study, synthesis of PtNPs were carried out using microbial cell lysate supernatant derived from various Gram-positive and Gram-negative bacteria such as *Pseudomonas kunmingensis* ADR19, *Psychrobacter faecalis* FZC6, *Vibrio fischeri* NRRL B-11177, *Jeotgalicoccus coquinae* ZC15, *Sporosarcina psychrophila* KC19, *Kocuria rosea* MN23 and *Pseudomonas putida* KT2440. The bacterial strains were cultivated at 30°C for 48 h at 200 rpm in Luria-Burtani broth (LB, tryptone 10 g/L, sodium chloride 10 g/L, yeast extract 5 g/L) medium and 1g of cell pellet was suspended in SDW and further sonicated for 5 min thrice at interval of 30 s. Cell debris were removed by centrifugation and the supernatant was filtered to obtain cell lysate supernatant (CLS). After adjusting the pH of the resulting CLS, $H_2PtCl_6 \cdot 7H_2O$ was mixed and incubated for 1 h at 90°C which led to the synthesis of PtNPs with average particle size of 3.95, 2.49, 3.84, 5.74, 4.24, 5.85 nm for *P. kunmingensis* ADR19, *P. faecalis* FZC6, *V. fischeri* NRRL B-11177, *J. coquinae* ZC15, *S. psychrophila* KC19, *K. rosea* MN23, respectively. The size of PtNPs synthesized from genetically engineered bacterium *P. putida* KT2440 was found to be 8.06 nm (Eramabadi et al., 2020).

MECHANISM BEHIND PtNPs Synthesis

Numerous mechanisms were reported for the bacterial synthesis of PtNPs which are depicted in **Figure 3**. Hydrogen gas was used as reducing agent during synthesis of PtNPs using bacterial cellulose (BC) from *Acetobacter xylinum*. The K_2PtCl_4 in solution undergoes solvolysis resulting in $PtCl_2(H_2O)_2$ and thus hydrogen bonding was found between oxygen atom of BC and hydrogen atom of $PtCl_2(H_2O)_2$ and vice versa. PtNPs were reduced on surface and inner side of BC membrane (Aritonang et al., 2014). *A. calcoaceticus* PUCM 1011 showed four protein bands with molecular mass 97, 66, 43 and 29 kDa, respectively that were responsible for synthesis of PtNPs. Hence, a multistep process was proposed to be involved in reduction of Pt(IV) to PtNPs intracellularly, that were later released due to rupture of the cell membrane leading to cell death. Bacterial proteins were also responsible for stabilization of the biogenic nanoparticles (Gaidhani et al., 2014). Synthesis of PtNPs by anaerobic sulfate reducing bacteria, *D. alaskensis* G20 was attributed to cytochromes and/or hydrogenases enzymes. After the formation they are exported to the outer surface of the cell hence forming extracellular PtNPs (Capness et al., 2015).

Another bacteria, *D. vulgaris* Hildenborough (DSM 644) encodes seven putative Hases enzymes out of which four are located in periplasm and three in cytoplasm. These enzymes might play a critical role in synthesis of PtNPs. The extracellular PtNPs strongly rationalize the fact that the periplasmic Hases were involved in reduction of metal ion into nanoparticle. Furthermore, bacterial surface may act as best nucleation site for metals adsorption hence supporting the deposition of NPs on cellular surface (Martins et al., 2016). *E. coli* MC4100 possesses various hydrogenases within cell that helps in catalyzing the

hydrogen into proton and electrons that may facilitate the biogenic synthesis of PtNPs (Attard et al., 2012).

Cyanobacteria such as *P. boryanum* UTEX 485 were also reported to synthesize PtNPs efficiently both intracellularly and extracellularly. Polysaccharides in the cell envelope with high uronic acid content provide carboxyl groups that facilitate binding of metal to the bacterial cell surface. Further, metallothioneins can bind to form metal-thiolate interactions due to sulphur rich amino acids in the polypeptides. Formation of dispersed PtNPs in *P. boryanum* might be attributed due to the entry of platinum into the cells as complexed $PtCl_4^0$ [Pt(IV)] that was successively reduced to Pt(II) and then to Pt(0) by cyanobacteria. Although, contact with the platinum(IV)-chloride reagent or the low pH and the high temperatures (60–180°C) immediately resulted in the death of the live biomass, the released metabolites might have played an essential role in the further synthesis and precipitation of PtNPs. Also, association of sulfur with bioreduced PtNPs indicated the involvement of organic sulphur and possibly organic phosphorus in the reduction and complexation of $PtCl_4^0$ (Lengke et al., 2006).

In other cyanobacteria reduction of metal salt to PtNPs occurred inside the heterocyst and vegetative cells followed by partial release of PtNPs into the medium. A reducing enzyme, nitrogenase is present in the cells which could be responsible for the reduction of platinum salt into PtNPs. Cyanobacteria possess two class of reducing enzymes, nitrogenase and hydrogenase. Nitrogenase is present in heterocysts of *Calothrix* and *Anabaena* which is responsible for the fixation of nitrogen from atmosphere. *Anabaena variabilis* produces two different nitrogenases which can function under either anaerobic or aerobic conditions present in heterocyst while other can function only in aerobic condition in heterocyst and vegetative cells. Hydrogenase reduces hydrogen ion into molecular hydrogen which may be involved in the reaction. Hence nitrogenase and hydrogenase can play a critical role for synthesis of PtNPs in cyanobacteria. *Leptolyngbya* does not possess heterocyst and fixes nitrogen only in dark hence gives less reduction efficiency. As the enzyme is found to be located in fibrous layer inside the heterocyst and thylakoids of vegetative cells, no PtNPs were observed in intra-thylakoid and intra-fibrous layer. Hence membrane controlled biomineralization might play a crucial role in controlled growth of PtNPs (Brayner et al., 2007).

S. algae synthesized PtNPs in periplasm and not in aqueous solution. Hence enzymes responsible for the reduction of $PtCl_6^{2-}$ might be localized in the periplasm. The synthesis of PtNPs using *S. algae* was thought to be a two-step process where initially the $PtCl_6^{2-}$ ion uptake from aqueous solution into periplasmic space occurred which was followed by enzymatic reduction of ions into PtNPs using lactate as electron donor within 60 min at pH 7 and 25°C (Konishi et al., 2007).

Riddin et al. (2010) reported involvement of two different hydrogenase enzymes for synthesis of PtNPs. Initially, the platinum(IV) was reduced to platinum(II) by a two-electron bioreduction using an oxygen tolerant/protected novel cytoplasmic hydrogenase. Second with the help of another two-electron bioreduction involving an oxygen sensitive

periplasmic hydrogenase, the platinum(II) ion was reduced to platinum(0) nanoparticles. Alternatively, the extracellular synthesis of PtNPs by *Streptomyces* sp. was attributed to the bacterial chloride reductase enzyme which is generally involved in nitric acid cycle and plays an important role in the reduction of chloride to chlorine. Nicotinamide adenine dinucleotide dependent chloride reductase enzyme might play a vital role in synthesis of PtNPs where the Pt ions were probably reduced via an electron shuttle enzymatic metal reduction process (Baskaran et al., 2017).

The proper proposed mechanism for the synthesis of nanoparticles by microorganism has not been conceived yet as different organism react differently during the synthesis of nanoparticles. Microorganism produces nanoparticles intracellularly and extracellularly. In intracellular synthesis, cell wall plays a crucial role in which electrostatic interaction of positive charge metal ion with negative charge cell wall takes place. The ion transport system transfer the ions inside the cell and the enzymes present inside the cell reduces the metal ions into nanoparticles. Many enzymes such as reductases, synthases, hydrolases and hydrogenases play role in synthesis and stabilization process. NADH and NADPH are commonly employed. In extracellular synthesis, microbial enzymes secreted in medium subsequently reduces metal ions into their respective nanoparticles and also they act as capping agent (Chaudhary et al., 2017).

APPLICATIONS OF BACTERIOGENIC PtNPs

Several unique features of PtNPs such as surface functionalities, size distribution, shape, surface area, composition, crystalline nature, catalytic, thermal and plasmonic properties, have led to their application in various fields. PtNPs have also been used for several biomedical applications such as anticancer, antiinflammatory, nanodiagnostic, antibacterial, photothermal and radiotherapy, drug delivery and bioimaging (Figure 4). Several types of NPs are used for drug delivery, most notably being carrier for delivery of antibiotics. The small and controllable size of NPs shows antimicrobial operations and combat intracellular bacteria. Several metallic NPs like Pt, Ag, Au, Pd, ZnO and Cu show negative zeta potential and hence cell damaging potential. PtNPs exhibit more negative zeta potential and cause damage to cells hence enhancing antibacterial activity. However, bacteriogenic PtNPs are explored till date for limited applications which are discussed in the following section.

TREATMENT OF PHARMACEUTICAL PRODUCTS

The PtNPs synthesized from *D. vulgaris* (DSM 644) showed excellent catalytic activity in removal of pharmaceutical products (PhP). Four different classes of PhP (ibuprofen, ciprofloxacin, sulfamethoxazole and 17 β -estradiol) are most relevant in the environment. PtNPs adsorbed 35% ciprofloxacin and 11% of both sulfamethoxazole and 17 β -estradiol and acted as

efficient biocatalyst in removal of PhPs. The efficiency of the adsorption was enhanced when the PtNPs catalysts were activated with hydrogen. After 24 h, 85% of sulfamethoxazole was removed at rate constant of 0.093 h⁻¹ by PtNPs while 70% of ciprofloxacin and 94% of 17 β -estradiol were removed with removal rate constants of 0.085 and 0.082 h⁻¹, respectively. Toxicity of the molecule produced from the reaction of PhP with PtNPs was checked by estrogenic activity. Low level of estrogenic activity was found (71%) aiding in production of less toxic products. It is important to note that only 13% of the catalytic activity was lost during recycling, which indicates the reusability of bacteriogenic PtNPs for technological development towards treatment of pharmaceutical effluent (Martins et al., 2016).

ANTICANCER ACTIVITY


The PtNPs synthesized from *Streptomyces* sp. exhibited promising anticancer activity against human breast cancer cell line (MCF-7). Treatment with PtNPs resulted in pronounced cellular deformity, detachment from the surface, and reduction in cell viability. In presence of bacteriogenic PtNPs only 52.77% cell viability was observed in MCF-7 human cell lines. IC₅₀ value was found to be 31.2 μ g/mL. Anticancer property of bacteriogenic PtNPs was found to be dose-dependent (Baskaran et al., 2017).

CATALYTIC ACTIVITY

Catalytic reduction of 4-nitrophenol (4-NP) and azo dyes were carried out using Pd-Pt alloys NPs synthesized from *S. oneidensis* MR-1. The peak centered of 4-NP was found near about 318 nm and was shifted to 400 nm after addition of NaBH₄. Pd-Pt alloys NPs were added which resulted in decrease in absorbance at 400 nm and increased at 300 nm indicating reduction of 4-NP to 4-aminophenol (4-AP). Within 4 min the reduction reaction was completed. It was concluded that Pd-Pt NPs located on surface of the biomass aided in transfer of electron from BH₄⁻ ions to nitro group of 4-NP. Azo dyes such as methyl orange (MO), methyl red (MR) and acid red 14 (AR 14) was used for the reduction reaction. The absorption peak was found at 465, 431 and 506 nm for MO, MR and AR 14 respectively. Upon addition of Pt-Pd alloys NPs, the absorbance of azo dyes were decreased within 2, 6, 13 min in case of MO, MR, AR 14 respectively (Xu et al., 2019). The catalytic efficiency of PtNPs synthesized in presence of AQDS was enhanced and the K_{app} value was 0.0065 min⁻¹ that might have attributed due to reduction in particle size (Tuo et al., 2016).

ANTIBACTERIAL AND ANTIOXIDANT

PtNPs synthesized by microbial cell lysate supernatant of various bacteria showed both antioxidant and antibacterial efficiency. The antioxidant potential was checked by 2,2-diphenyl-1-picrylhydrazyl (DPPH) radical scavenging activity whereas the minimum inhibitory concentration (MIC) was used to check antimicrobial property. Purple color of DPPH was converted to



pale yellow in the presence of PtNPs hence indicating that PtNPs participates in transferring of electron/hydrogen and neutralizes the DPPH radical. The antioxidant activity was found to be dose-dependent. At 1000 $\mu\text{g}/\text{mL}$ concentration of PtNPs, various microbial strains showed different antioxidant activity. Highest antioxidant activity was observed in strain ZC15 followed by FZC6, CCV1, NRRL B-11177, KC19, KT2440, ADR19 and at lowest MN23. DPPH free radical scavenging activity up to 95% was observed in ZC15 and FZC6 while 70% activity was seen in case of NRRL B-11177, KC19, KT2440 and CCV1 strains.

The antimicrobial activity was checked against *E. coli* and *S. aureus*. It was observed that, the surface electrical charge of NPs has significant impact in antibacterial activity. The zeta potential of synthesized PtNPs from Gram-negative organisms was found to be -36.88 , -29.37 and -21.60 mV for strains named ADR19, FZC6 and NRRL B-11177, respectively and for Gram-positive it was -35.64 , -30.90 and -26.08 mV for strains ZC15, KC19 and MN23 respectively. The zeta potential of genetically engineered bacterium was -20.37 mV. Although, PtNPs synthesized from NRRL B-11177 and KT2440 with similar zeta potential showed different activity against *S. aureus* and *E. coli*. This difference might be because of different size of NPs and peptidoglycan layer. The smaller size of PtNPs synthesized from NRRL B-1117 (3.84 nm) was easily able to pass through cell wall of *S. aureus* and cause reactive oxygen species (ROS) production, hence resulted in better antibacterial activity (Eramabadi et al., 2020).

SCOPE AND FUTURE APPLICATIONS

Although, physically and chemically synthesized PtNPs are used for various applications in catalysis and sensors, biologically synthesized PtNPs are yet to be explored for multivariate applications that are depicted in **Figure 4**. Hence, there is a need for critical consideration of using the greener path for synthesis of PtNPs. Bacteriogenic PtNPs can be used to develop amperometric gas sensor for hydrogen by electrodepositing on gold microchannel electrodes. Similarly, heavy metal ion sensors can be designed for environmental monitoring by depositing bacteriogenic PtNPs on tantalum substrate using ion beam sputtering deposition (IBSD) technique (Hussain et al. 2019). Implantable amperometric biosensors can be designed by immobilizing enzymes like glutamate oxidase on electrodes composed of bacteriogenic PtNPs, multi-walled carbon nanotubes and suitable conducting polymers. These types of sensors can be used for glutamate monitoring during traumatic injury (Nguyen et al. 2019). Further, bacteriogenic PtNPs should also be checked for catalytic combustion of hydrocarbon and oxygenated fuels for providing alternative power source for portable electronic devices. In this respect, it would be of utmost interest to evaluate the catalytic potential of these biogenic PtNPs to yield self-ignition and stable combustion from methanol-air mixtures (Guggilla et al. 2019).

Many bacteria synthesize PtNPs intracellularly or the particles are present in the periplasmic space of the bacterial cells. Similarly, in some cases the PtNPs are strongly bound to the cell surface. Hence, the recovery of the nanoparticles after synthesis is also another aspect which is needed to be addressed.

The rational optimization of the process parameters can overcome the aforementioned drawbacks. Firstly, the strain selection, which is most crucial for getting the PtNPs of desired dimension. Secondly, the cell passage and density and the reaction conditions (such as temperature, pH, aeration, agitation and concentration of metal salts), which should be optimized in order to ensure the reproducibility of the morphological features of bacteriogenic PtNPs. Various physical disruption methods such as grinding, mechanical disruption, freeze-thaw cycles, liquid homogenization, and sonication can be applied for recovery of the PtNPs by lysis of the cells. Similarly, chemical agents like organic solvents (e.g., alcohols, ether, and chloroform), chelating agents (EDTA), detergents or surfactants (e.g., SDS, Triton) and chaotropic agents (e.g., urea, guanidine) can be employed for bacterial cell lysis (Islam et al. 2017). Also the porosity of the bacterial cells can be increased by treating with calcium chloride so that the intracellular PtNPs can be tapped.

Another important aspect is application of genetic engineering and/or recombinant DNA technology to develop industrially important bacterial strains with high and efficient PtNPs producing ability. Such strain improvement method will increase the platinum metal salt tolerance of the bacteria, platinum ion adsorbing ability, and enhanced platinum ion reducing efficiency.

Although silver and gold nanoparticles from bacteria have been extensively studied for their therapeutic applications, only few studies have been reported for bacteriogenic PtNPs. Antibacterial, antifungal, antibiofilm, antiprotozoal, anticancer, antioxidant, anti-inflammatory and wound healing properties of bacteriogenic PtNPs should be explored. Similarly, thorough *in-vitro* and *in-vivo* toxicity studies must be performed to ensure that no adverse effects are caused during therapeutic applications. Thus, there is a huge scope of further research to explore bacteriogenic PtNPs and their applications.

CONCLUSION

PtNPs have numerous applications in catalysis and fuel cell, while it has recently gained much attention for biomedical applications that include nanozymes, nanocarriers, nanosensors. Multifunctionalized

PtNPs may prove to be efficient theranostic agent (with combined functionality for therapy and diagnosis). In this review we have compared the advantages and disadvantages of bacteriogenic synthesis of PtNPs with that of the other conventional physical and chemical methods. However, till date limited bacterial diversity has been exploited for the synthesis of PtNPs which is an environmentally benign rapid and efficient process. The enzymatic and non-enzymatic processes employed by bacterial cell for reduction of the Pt ions to PtNPs offer a better control over size distribution, shape and crystallinity. Furthermore, we discussed the toxicological effects, biomedical applications, and use of PtNPs in therapy and waste treatment. Although, bacteriogenic PtNPs exhibit high efficacy with low concentrations, several factors still need to be considered before it can be used as a nanomedicine that include type of precursor, the method of production, stability, solubility, biodistribution, controlled release, bioaccumulation, cell-specific targeting, retention and toxicological issues to human beings. The future of bacteriogenic PtNPs in biomedical applications holds great promise, especially in the area of drug delivery, targeted therapy, early disease diagnosis, cellular and deep tissue imaging, gene delivery, as well as multifunctional therapeutics. In view of the background, it can be concluded that in future, multifunctional bacteriogenic PtNPs would be promising candidate for biomedical applications as novel nanomedicine.

AUTHOR CONTRIBUTIONS

KB and SG wrote the initial draft of the manuscript. KP and CS participated in the writing of the manuscript. SG conceived the idea, designed and wrote the manuscript. KP, CS, and SG revised and finalized the manuscript.

FUNDING

SG is thankful to Department of Biotechnology (DBT), Ministry of Science and Technology, Government of India for funding (BT/IN/Indo-US/Foldscope/39/2015). CS acknowledges University of Catania (call: Piano della Ricerca di Ateneo, Linea di Intervento2, 2018–2020 and GRABIO projects).

REFERENCES

- Aritonang, H. F., Onggo, D., Ciptati, C., and Radiman, C. L. (2014). Synthesis of platinum nanoparticles from K_2PtCl_4 solution using bacterial cellulose matrix. *J. Nanoparticles Article ID*. 285954, 1–6. doi:10.1155/2014/285954
- Attard, G., Casadesús, M., Macaskie, L. E., and Deplanche, K. (2012). Biosynthesis of platinum nanoparticles by *Escherichia coli* MC4100: can such nanoparticles exhibit intrinsic surface enantioselectivity?. *Langmuir*. 28 (11), 5267–5274. doi:10.1021/la204495z
- Baskaran, B., Muthukumarasamy, A., Chidambaram, S., Sugumaran, A., Ramachandran, K., and Rasu Manimuthu, T. (2017). Cytotoxic potentials of biologically fabricated platinum nanoparticles from *Streptomyces sp.* on MCF-7 breast cancer cells. *IET Nanobiotechnol.* 11 (3), 241–246. doi:10.1049/iet-nbt.2016.0040
- Bonnemann, H., and Richards, R. M. (2001). Nanoscopic metal particles—synthetic methods and potential applications. *Eur. J. Inorg. Chem.* 2001, 2455–2480. doi:10.1002/1099-0682(200109)2001:10<2455::AID-EJIC2455>3.0.CO;2-Z
- Brayner, R., Barberousse, H., Hemadi, M., Djedjat, C., Yéprémian, C., Coradin, T., et al. (2007). Cyanobacteria as bioreactors for the synthesis of Au, Ag, Pd, and Pt nanoparticles via an enzyme-mediated route. *J. Nanosci. Nanotechnol.* 7 (8), 2696–2708. doi:10.1166/jnn.2007.600
- Capeness, M. J., Edmundson, M. C., and Horsfall, L. E. (2015). Nickel and platinum group metal nanoparticle production by *Desulfovibrio alaskensis* G20. *N Biotechnol.* 32 (6), 727–731. doi:10.1016/j.nbt.2015.02.002

- Chaudhary, D., Kumar, R., Kumari, A., and Rashmi, J. R. (2017). "Biosynthesis of nanoparticles by microorganisms and their significance in sustainable agriculture," in *Probiotics in agroecosystem*. Editors V. Kumar, M. Kumar, S. Sharma, and R. Prasad (Singapore: Springer), 93–115. doi:10.1007/978-981-10-4059-7_5
- Cueto, M., Sanz, M., Oujja, M., Gamez, F., Haya, M. B., and Castillejo, M. (2011). Platinum nanoparticles prepared by laser ablation in aqueous solutions: fabrication and application to laser desorption ionization. *J. Phys. Chem. C* 115, 22217–22224. doi:10.1021/jp207324h
- Dhand, C., Dwivedi, N., Loh, X. J., Ying, A., Verma, N., Beuerman, R. W., et al. (2015). Methods and strategies for the synthesis of diverse nanoparticles and their applications: a comprehensive overview. *RSC Adv.* 5, 105003–105037. doi:10.1039/C5RA19388E
- Eramabadi, P., Masoudi, M., Makhdomi, A., and Mashreghi, M. (2020). Microbial cell lysate supernatant (CLS) alteration impact on platinum nanoparticles fabrication, characterization, antioxidant and antibacterial activity. *Mater. Sci. Eng. C* 117, 111292. doi:10.1016/j.msec.2020.111292
- Gahlawat, G., and Choudhury, A. R. (2019). A review on the biosynthesis of metal and metal salt nanoparticles by microbes. *RSC Adv.* 9, 12944. doi:10.1039/C8RA10483B
- Gaidhani, S. V., Yeshvekar, R. K., Shedbalkar, U. U., Bellare, J. H., and Chopade, B. A. (2014). Bio-reduction of hexachloroplatinic acid to platinum nanoparticles employing *Acinetobacter calcoaceticus*. *Process Biochem.* 49 (12), 2313–2319. doi:10.1016/j.procbio.2014.10.002
- Gautam, A., Guleria, P., and Kumar, V. (2020). Platinum nanoparticles: synthesis strategies and applications. *Nanoarchitectonics*. 1 (2), 70–86. doi:10.37256/nat.122020286
- Ghosh, S., Nitnavare, R., Dewle, A., Tomar, G. B., Chippalkatti, R., More, P., et al. (2015). Novel platinum-palladium bimetallic nanoparticles synthesized by *Dioscorea bulbifera*: anticancer and antioxidant activities. *Int. J. Nanomedicine*. 10 (1), 7477–7490. doi:10.2147/IJN.S91579
- Ghosh, S., Shah, S., and Webster, T. J. (2020). "Recent trends in fungal mediated biosynthesis of nanoparticles," in *Fungi bio-prospects in sustainable agriculture, environment and nano-technology*. Editors M. P. Shah, V. K. Sharma, S. Parmar, and A. Kumar. New York: Elsevier.
- Ghosh, S., and Webster, T. J. (2020a). "Viruses and nanotechnology," in *Nanobiotechnology: microbes and plant assisted synthesis of nanoparticles, mechanisms and applications*. Editors S. Ghosh and T. J. Webster. New York: Elsevier.
- Ghosh, S., and Webster, T. J. (2020b). "Biologically synthesized nanoparticles for dye removal," in *Removal of emerging contaminants from wastewater through bio-nanotechnology*. Editors M. Shah, S. R. Couto, and J. K. Biswas. New York: Elsevier.
- Guggilla, B. R., Rusted, A., and Bakrania, S. (2019). Platinum nanoparticle catalysis of methanol for thermoelectric power generation. *Appl. Energy*. 237, 155–162. doi:10.1016/j.apenergy.2018.12.083
- Hussain, G., Ge, M., Zhao, C., and Silvester, D. S. (2019). Fast responding hydrogen gas sensors using platinum nanoparticle modified microchannels and ionic liquids. *Anal. Chim. Acta*. 1072, 35–45. doi:10.1016/j.aca.2019.04.042
- Islam, M. S., Aryasomayajula, A., and Selvaganapathy, P. R. (2017). A review on macroscale and microscale cell lysis methods. *Micromachines*. 8, 83. doi:10.3390/mi8030083
- Jeyaraj, M., Gurunathan, S., Qasim, M., Kang, M. H., and Kim, J. H. (2019). A comprehensive review on the synthesis, characterization, and biomedical application of platinum nanoparticles. *Nanomaterials*. 9 (12), 1719. doi:10.3390/nano9121719
- Konishi, Y., Ohno, K., Saitoh, N., Nomura, T., Nagamine, S., Hishida, H., et al. (2007). Bioreductive deposition of platinum nanoparticles on the bacterium *Shewanella algae*. *J. Biotechnol.* 128 (3), 648–653. doi:10.1016/j.jbiotec.2006.11.014
- Kyung Tae, K., Sung-Ho, J., Seung-Cheol, C., and Deog-Su, P. (2013). Green synthesis of platinum nanoparticles by electroreduction of a K_2PtCl_6 solid-state precursor and its electrocatalytic effects on H_2O_2 reduction. *Bull. Korean Chem. Soc.* 34, 3835–3839. doi:10.5012/bkcs.2013.34.12.3835
- Lengke, M. F., Fleet, M. E., and Southam, G. (2006). Synthesis of platinum nanoparticles by reaction of filamentous cyanobacteria with platinum(IV)-chloride complex. *Langmuir*. 22 (17), 7318–7323. doi:10.1021/la060873s
- Liu, Z. L., Lee, J. Y., Han, M., Chen, W. X., and Gan, L. M. (2002). Synthesis and characterization of PtRu/C catalysts from microemulsions and emulsions. *J. Mater. Chem.* 12, 2453–2458. doi:10.1039/b200875k
- Mafune, F., and Kondow, T. (2004). Selective laser fabrication of small nanoparticles and nano-networks in solution by irradiation of UV pulsed laser onto platinum nanoparticles. *Chem. Phys. Lett.* 383, 343–347. doi:10.1016/j.cplett.2003.10.149
- Martins, M., Mourato, C., Sanches, S., Noronha, J. P., Crespo, M. T., and Pereira, I. A. (2016). Biogenic platinum and palladium nanoparticles as new catalysts for the removal of pharmaceutical compounds. *Water Res.* 108, 160–168. doi:10.1016/j.watres.2016.10.071
- Naseer, A., Ali, A., Ali, S., Mahmood, A., Kusuma, H. S., Nazir, A., et al. (2020). Biogenic and eco-benign synthesis of platinum nanoparticles (Pt NPs) using plants aqueous extracts and biological derivatives: environmental, biological and catalytic applications. *J. Mater. Res. Technol.* 9 (4), 9093–9107. doi:10.1016/j.jmrt.2020.06.013
- Nguyen, T. N. H., Nolan, J. K., Park, H., Lam, S., Fattah, M., Page, J. C., et al. (2019). Facile fabrication of flexible glutamate biosensor using direct writing of platinum nanoparticle-based nanocomposite ink. *Biosens. Bioelectron.* 131, 257–266. doi:10.1016/j.bios.2019.01.051
- Nichols, W. T., Sasaki, T., and Koshizaki, N. (2006). Laser ablation of a platinum target in water. III. Laser-induced reactions. *J. Appl. Phys.* 100, 114911. doi:10.1063/1.2390640
- Park, D. K., Lee, S. J., Lee, J., Choi, M. Y., and Han, S. W. (2010). Effect of polymeric stabilizers on the catalytic activity of Pt nanoparticles synthesized by laser ablation. *Chem. Phys. Lett.* 484, 254–257. doi:10.1016/j.cplett.2009.11.031
- Patel, P., and Ponnuchamy, K. (2019). A perspective on biogenic synthesis of platinum nanoparticles and their biomedical applications. *Spectrochim. Acta Mol. Biomol. Spectrosc.* 211, 94–99. doi:10.1016/j.saa.2018.11.047
- Riddin, T., Gericke, M., and Whiteley, C. G. (2010). Biological synthesis of platinum nanoparticles: effect of initial metal concentration. *Enzyme Microb. Technol.* 46 (6), 501–505. doi:10.1016/j.enzmictec.2010.02.006
- Riddin, T. L., Govender, Y., Gericke, M., and Whiteley, C. G. (2009). Two different hydrogenase enzymes from sulphate-reducing bacteria are responsible for the bioreductive mechanism of platinum into nanoparticles. *Enzyme Microb. Technol.* 45 (7), 267–273. doi:10.1016/j.enzmictec.2009.06.006
- Rokade, S., Joshi, K., Mahajan, K., Patil, S., Tomar, G., Dubal, D., et al. (2018). *Gloriosa superba* mediated synthesis of platinum and palladium nanoparticles for induction of apoptosis in breast cancer. *Bioinorg. Chem. Appl.*, 2018, 4924186. doi:10.1155/2018/4924186
- Rokade, S. S., Joshi, K. A., Mahajan, K., Tomar, G., Dubal, D. S., Parihar, V. S., et al. (2017). Novel anticancer platinum and palladium nanoparticles from *Barleria prionitis*. *Glob. J. Nanomedicine*. 2 (5), 555600. doi:10.19080/GJN.2017.02.555600
- Srivastava, S. K., and Constanti, M. (2012). Room temperature biogenic synthesis of multiple nanoparticles (Ag, Pd, Fe, Rh, Ni, Ru, Pt, Co, and Li) by *Pseudomonas aeruginosa* SM1. *J. Nanopart. Res.* 14 (831), 1–10. doi:10.1007/s11051-012-0831-7
- Stepanov, A. L., Golubev, A. N., Nikitin, S. I., and Osin, Y. N. (2014). A review on the fabrication and properties of platinum nanoparticles. *Rev. Adv. Mater. Sci.* 38, 160–175. doi:10.1016/j.nano.2009.07.002
- Thakkar, K. N., Mhatre, S. S., and Parikh, R. Y. (2010). Biological synthesis of metallic nanoparticles. *Nanomedicine*. 6, 257–262. doi:10.1016/j.nano.2009.07.002
- Tuo, Y., Liu, G., Dong, B., Yu, H., Zhou, J., Wang, J., et al. (2016). Microbial synthesis of bimetallic PdPt nanoparticles for catalytic reduction of 4-nitrophenol. *Environ. Sci. Pollut. Res. Int.* 24, 5249–5258. doi:10.1007/s11356-016-8276-7
- Xu, H., Xiao, Y., Xu, M., Cui, H., Tan, L., Feng, N., et al. (2019). Microbial synthesis of Pd–Pt alloy nanoparticles using *Shewanella oneidensis* MR-1 with enhanced catalytic activity for nitrophenol and azo dyes reduction. *Nanotechnology*. 8 (30), 065607. doi:10.1088/1361-6528/aaf2a6

Conflict of Interest: The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

Copyright © 2021 Bloch, Pardesi, Satriano and Ghosh. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) and the copyright owner(s) are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.