



# Zn-Based Deep Eutectic Solvent as the Stabilizing Electrolyte for Zn Metal Anode in Rechargeable Aqueous Batteries

Gaurav M. Thorat, Van-Chuong Ho and Junyoung Mun\*

Department of Energy and Chemical Engineering, Incheon National University, Incheon, South Korea

Owing to its low cost and high safety, metallic zinc has received considerable attention as an anode material for zinc aqueous batteries (ZIBs). However, the Zn metal instability as a result of ultrafast and obstinate dendrite formation, free-water-induced parasite reactions, and corrosive electrolytes has detrimental effects on the implementation of ZIBs. We present an alternative stable electrolyte for ZIBs based on a zinc chloride/ethylene glycol deep eutectic solvent (DES). This electrolyte consists of abundant low-cost materials and a utilizable  $\text{Zn}^{2+}$  concentration of approximately 1 M. It combines the advantages of the aqueous and DES media to provide safe and reversible Zn plating/stripping with a two-fold increase in the cycling life compared to that of conventional aqueous electrolytes. With these advantages, the Zn symmetric cell operates at  $0.2 \text{ mA cm}^{-2}$  for 300 h. Due to its high efficiency and compositional versatility, this electrolyte enables the investigation of a non-aqueous electrolyte family for ZIBs that fulfill grid-scale electrical energy storage requirements.

**Keywords:** Zn anode, deep eutectic solvent, electrolyte, zinc ion batteries (ZIBs), des

## OPEN ACCESS

### Edited by:

Wenhui Wang,  
Harbin Institute of Technology,  
Shenzhen, China

### Reviewed by:

Yikang Yu,  
Purdue University, United States  
Xingxing Gu,  
Chongqing Technology and Business  
University, China

### \*Correspondence:

Junyoung Mun  
jymun@inu.ac.kr

### Specialty section:

This article was submitted to  
Electrochemistry,  
a section of the journal  
Frontiers in Chemistry

**Received:** 30 November 2021

**Accepted:** 27 December 2021

**Published:** 14 January 2022

### Citation:

Thorat GM, Ho V-C and Mun J (2022)  
Zn-Based Deep Eutectic Solvent as  
the Stabilizing Electrolyte for Zn Metal  
Anode in Rechargeable  
Aqueous Batteries.  
Front. Chem. 9:825807.  
doi: 10.3389/fchem.2021.825807

## INTRODUCTION

Zinc-ion batteries (ZIBs) have attracted worldwide interest for their application in next-generation energy storage devices due to their notable characteristics, such as cost effectiveness, eco-friendliness, high safety, resource abundance, high volumetric capacity, and aqueous electrolyte compatibility (Hu et al., 2020; Wang et al., 2020a; Hansen and Liu, 2021). The electrolytes in ZIBs are essential components that play a critical role in their electrochemical behavior (Zhang et al., 2020). They provide a steady electrochemical potential window, channel between the anode and the cathode for Zn movement, and aid in determining the reaction mechanism and the ionic conductivity (IC) (Zhu et al., 2021). ZIBs with aqueous electrolytes possess several benefits, such as high energy density (Wu et al., 2021b), safety, and stability over a high number of cycles, as well as ecological benignity (Zhang et al., 2018b; Mo et al., 2019; Zhu et al., 2019). However, accompanying these advantages are some difficulties as well. During electrochemical cycling in alkaline electrolytes, significant amounts of dendritic growth and/or by-products, such as ZnO and  $\text{Zn}(\text{OH})_2$ , accumulate on the Zn surface, preventing further application due to low Coulombic efficiencies (CEs) and rapid capacity fading. In neutral or mildly acidic aqueous electrolytes, the Zn anode is primarily concerned with hydrogen evolution, electrolyte breakdown due to the small potential window of water (1.23 V), and Zn electrode passivation, all of which affect the battery efficiency (Zhang et al., 2020; Liu et al., 2021). The use of water-in-salt (WIS) electrolytes, such as highly concentrated Zn-TFSI,  $\text{ZnCl}_2$ , LiTFSI/Zn

$[\text{N}(\text{SO}_2\text{CF}_3)_2]_2$ ,  $\text{LiN}(\text{SO}_2\text{CF}_3)_2$ , and  $\text{LiN}(\text{SO}_2\text{CF}_3)_2/\text{CF}_3\text{SO}_3\text{Li}$ , offers an excellent strategy for engineering a high-stability Zn anode by forming a solvation sheath structure of the  $\text{Zn}^{2+}$  cation, which eliminates any water-induced side reactions (Zhang et al., 2018a; Zhao et al., 2019; Kao-ian et al., 2021). Another advantage of WIS electrolytes over dilute electrolytes is the thermodynamically shifted potential equilibrium of the cation-intercalation reaction. However, these WIS solutions contain a high proportion of fluorinated salts, which limits their practical viability owing to their high cost and toxicity. Another inorganic additive MXene nanosheets in the electrolyte significantly decreased  $\text{Zn}^{2+}$  diffusion paths and aided migration, and the numerous functional groups and high conductivity caused uniform nucleation (Du et al., 2021; Sun et al., 2021). In comparison to organic and inorganic additives, the organic polymer additives effectively control electrodeposition rate however their synthesis is tedious (Du et al., 2021; Wu et al., 2021a). Therefore, these issues associated with electrolytes must be addressed before ZIBs can be effectively used on a large scale.

Another potentially viable electrolyte is a room-temperature ionic liquid (RTIL) electrolyte, which exhibits several desirable properties, such as a high IC, good dissolving ability, wide potential window, low volatility, and nonflammability. For example, dendrite-free plating/stripping (>1,500 h) and 100% CE were achieved using an IL-based Zn salt electrolyte. Traditional RTILs, imidazolium-based ionic liquids, exhibit an excellent Zn electrodeposition performance as well as an exceptional electrochemical window (>4 V) (Kazemiabnavi et al., 2016). However, RTILs have proven to be expensive and extremely susceptible to moisture, making large-scale production of ZIBs using RTIL impossible (Abbott et al., 2008; Abbott et al., 2013). In this context, a promising and innovative ionic fluid, a deep eutectic solvent (DES) analogous to an ionic liquid, is rapidly emerging in the field of Li-ion battery electrolytes. DESs are formed by mixing two or more components in proper molar ratios simultaneously, resulting in a eutectic mixture via hydrogen bonding. Due to their high viscosity, conductivity, surface tension, and biodegradability, DESs are considered as green solvents (Thorat et al., 2018).

Herein, we report the development of a cost-effective, environmentally friendly, and intrinsically safe  $\text{ZnCl}_2$ -4 ethylene glycol (EG) deep eutectic composition ( $\text{ZnCl}_2$ -4EG DES) as an electrolyte for Zn anodes in ZIBs. The properties of EG, which acts as a water blocker to generate a confined high-concentration electrolyte (Wang et al., 2020b; Xu and Jiang, 2021), and  $\text{ZnCl}_2$ , which was previously used as a WIS electrolyte for a dendrite-free Zn metal anode, make them ideal components for DESs used as electrolytes for ZIBs. Furthermore, early reports indicate that  $\text{ZnCl}_2$ -based DESs have potential applications in electrochemistry. In particular, the  $\text{ZnCl}_2$ -4EG DES has been previously used in electrochemical processes (Abbott et al., 2007a). When tested for the Zn symmetric cell, this electrolyte combines the advantages of both aqueous and DES media to enable safe and reversible Zn plating/stripping with a two-fold increase in the cycling life compared to that of conventional aqueous electrolytes.

## EXPERIMENTAL SECTION

### Materials

Ethylene glycol (EG) ( $\text{HOCH}_2\text{CH}_2\text{OH}$ , > 99.5%, hydrogen bond donor (HBD)) and Zinc chloride ( $\text{ZnCl}_2$ , > 99.9%, hydrogen bond acceptor (HBA)) were procured from Sigma Aldrich (South Korea) and used without further purification. Zn foil (99.995%, Alfa Aesar, South Korea) with a thickness of 0.025 cm was used.

### Deep Eutectic Solvent Electrolyte Preparation

DESs were formed by mixing  $\text{ZnCl}_2$  and EG in a specified molar ratio (1:4) and heating at  $100^\circ\text{C}$  for 1 h at air pressure under steady magnetic stirring until a homogeneous liquid was obtained. In subsequent discussion, the synthesized electrolyte will be referred to as the ZE DES. Finally, the synthesized DES solution was sealed and placed in a transparent glass bottle for later use. The decrease in the  $T_m$  of the mixture is caused by charge delocalization due to hydrogen bonding between the halide anion and EG.

### Characterization of Materials

Fourier transform infrared spectra were recorded on a PerkinElmer Spectrum Two ATR instrument over a range of  $4,000$ – $400\text{ cm}^{-1}$ . The thermal stability of the ZE electrolyte was analyzed using thermogravimetric analysis (TGA). TGA was performed on a Scinco TGA-N 1500 instrument over a range of  $30$ – $800^\circ\text{C}$  under nitrogen flow at a scanning rate of  $10^\circ\text{C min}^{-1}$ . Differential scanning calorimetry (DSC) was carried out using PerkinElmer DSC 4000.

### Assembly of Symmetric Cells


Two bare Zn foil electrodes with a diameter of 12 mm each were assembled into CR2032-type coin cells. A  $\text{ZnCl}_2$ -4EG DES was used as the electrolyte, and glass fiber filters served as separators. The cells were then sealed in air.

### Electrochemical Tests


To explore the electrochemical behavior of Zn foils, galvanostatic charging-discharging cycling was performed at a current density and total capacity of  $0.2$ – $2$  and  $0.5$ – $2\text{ mAh cm}^{-2}$ , respectively. The cycling performance was evaluated using a standard eight-channel WonA-Tech battery test system (South Korea). Cyclic voltammetry (CV) was conducted to evaluate the electrochemical behavior of the Zn anode in an electrode cell with glassy C, Pt wire, and Ag wire serving as the working, counter, and reference electrodes, respectively. A ZE DES was used as the electrolyte.

## RESULTS AND DISCUSSION

First, the  $\text{ZnCl}_2$ -based eutectic solvent used was prepared by simply mixing  $\text{ZnCl}_2$  with EG in a 1:4 mole ratio and stirring at  $100^\circ\text{C}$  until a transparent liquid, named as ZE DES, was formed. The preparation methodology for the ZE DES is shown in



**FIGURE 1 |** (A) Synthesis scheme for the preparation of the  $ZnCl_2$ -4EG DES electrolyte. (B,C) Schematic and photographs of the ZE DES electrolyte.





**FIGURE 2 |** (A) Fourier transform infrared spectra of neat ethylene glycol,  $ZnCl_2$ , and their eutectic mixture (ZE DES). (B) -OH and (C) -methylene stretching regions.

**Figure 1A.** The molar fraction between  $ZnCl_2$  and EG was chosen to be 1:4, as it forms the most stable structure relative to other molar fractions via the formation of a special molecular packing (Tran and Thi Hang, 2018; Kalhor et al., 2021). The larger clusters of EG disintegrate into smaller ones upon mixing with  $ZnCl_2$ , and  $ZnCl_2$ -EG complexes are formed. Theoretical calculations indicated that EG molecules interacted with  $ZnCl_2$  via the production of both O-H-Cl hydrogen bonds and Zn-O coordination bonds (Figure 1B).  $ZnCl_2$  is a linear molecule with a 180° Cl-Zn-Cl angle. Upon mixing with EG, the hydroxyl groups of EG engage with the Zn metal atoms, thereby decreasing the Cl-Zn-Cl angles. As a result, the Zn-Cl bond length increases with increasing EG concentration, which is noteworthy. This is due to the partly ionic character of  $ZnCl_2$ , and therefore, the high EG content in the complexes causes a decrease in the electron density at the Zn-Cl bond critical point. As a result, the Zn-Cl bond tends to

dissociate in the  $ZnCl_2$ -based DES resulting in high electrical conductivity compared to that of EG (Sarjuna and Ilangeswaran, 2020; Kalhor et al., 2021). The ZE DES used in this study has a freezing point lower than room temperature, making it suitable for a variety of room-temperature applications. In general, the natures and molar compositions of the metal salt ( $ZnCl_2$ ) and the HBD (i.e., EG) affect the physical and chemical features of deep eutectics. The formed ZE DES displayed a colorless, transparent, and uniform state without any additional aqueous solution (Figure 1C).


As previously mentioned, the ZE DES exhibited a diverse range of interactions, including hydrogen bonding, electrostatic interactions, and dispersion. Among these, hydrogen bonding interactions have received significant attention. Owing to the exceptional sensitivity of IR to hydrogen bonding interactions, FT-IR spectra were acquired to investigate the chemical bond structures in the DESs. Figure 2A shows the infrared absorption



spectra of the ZE DES, pure EG, and  $\text{ZnCl}_2$ . The total infrared spectrum of ZE DES is identical to that of  $\text{ZnCl}_2$  and EG, but with a frequency shift in the  $\nu(\text{O-H})$  and  $(\text{C-H})$  regions. These findings indicate that the EG structure was not destroyed during the DES formation process. For pure EG, the broad band centered at  $3,288\text{ cm}^{-1}$  in the  $\nu(\text{O-H})$  region extending from  $3,040$  to  $3,620\text{ cm}^{-1}$  is strongly related to the extensive hydrogen bonding network. The two bands in the  $(\text{C-H})$  region at  $2,860$  and  $2,941\text{ cm}^{-1}$  are attributed to the  $s(\text{C-H})$  and  $as(\text{C-H})$  of methylene, respectively. The peaks at  $1,026\text{ cm}^{-1}$  can be attributed to the stretching vibrations of the  $\text{C-C-O}$  bonds (Hong et al., 2016; Kalthor et al., 2021). When  $\text{ZnCl}_2$  was added, the band shapes, positions, and intensities changed significantly.

The strong Peak in  $\text{ZnCl}_2$  at  $1,608\text{ cm}^{-1}$  is assigned to  $\nu(\text{H-OH})$  which may originate from the absorption of water by highly hygroscopic zinc chloride during FTIR measurement. Its position depends on hydration number of  $\text{ZnCl}_2$ . The presence of such prominent peak has been also confirmed in the study of crystalline and liquid structure hydration number ( $R$ ) (Wilcox et al., 2015). However, DES synthesis is carried out at higher temperature and subsequent storage is strictly controlled where exposure the water to DES is minimum. As result the Peak at  $1,608\text{ cm}^{-1}$  resulted into diminishing the intensity with blue shift at  $1,647\text{ cm}^{-1}$  (reduction in hydration number in  $\text{ZnCl}_2$ ) upon DESs formation which can clearly see from the enlarge portion of corresponding region of IR depicted in **Supplementary Figure S1** (Electronic supplementary information; ESI).


In the  $\nu(\text{O-H})$  region, the  $-\text{O-H}$  stretching peak shifts to a wavenumber lower than  $3,288\text{ cm}^{-1}$  (**Figure 2B**). Furthermore, the stretching  $(\text{C-H})$  and asymmetric stretching  $(\text{C-H})$  bands are blue-shifted by 5 and  $10\text{ cm}^{-1}$ , respectively (**Figure 2C**). These results show that  $\text{ZnCl}_2$  has a significant impact on the hydrogen bonding characteristics of EG. These blue and red shifts of the IR bands are typically linked to the strength variations of the respective hydrogen bonds in the corresponding molecules. A red shift in the band indicates stronger hydrogen bonds, while a blue shift indicates weaker hydrogen bonds for appropriate




hydrogen bonding (McDowell, 2003; Sanchora et al., 2019). However, for an improper hydrogen bond forming group, the band shifts were in the reverse direction. Since the  $\text{C-H}$ s of EG are inappropriate hydrogen bond-formation groups, the blue shifts represent stronger hydrogen bonds in ZE DES than those in pure EG.

TGA and DSC measurements of the ZE DES were conducted to investigate the thermal characteristics of the electrolyte under study. The DSC measurement results of the ZE DES electrolyte are shown in **Figure 3**. In the ZE DES electrolyte, there was no discernible peak corresponding to the melting point of EG ( $-12^{\circ}\text{C}$ ) (Kaur et al., 2018), indicating that deep eutectics were formed in the absence of unreacted starting components. Therefore, the quantitative generation of deep eutectics through the combination of metal salt and alcohol, for example, EG, could be crucial for lowering the melting temperature.

**Figure 4** shows the TGA results of ZE DES. The electrolyte exhibits the greatest weight loss between  $200$  and  $400^{\circ}\text{C}$ , making it



**FIGURE 6** | Stripping/plating performance of the Zn metal anode in the ZE electrolyte at different current densities: **(A)** 0.2 mA cm<sup>-2</sup> and **(B)** first five cycles at 0.2 and 0.4 mA cm<sup>-2</sup>.




**FIGURE 7** | Long-term stripping/plating performance of the Zn metal anode at 0.2 mA cm<sup>-2</sup> in **(A)** ZE electrolyte and **(B)** aqueous 1 M ZnSO<sub>4</sub>, and **(C)** at the 1 mA cm<sup>-2</sup> for ZE electrolyte. **(D)** Digital photographs of the Zn foil acquired after 50 cycles at 0.2 mA cm<sup>-2</sup>.

suitable for high-temperature applications. At temperatures close to the boiling point of pure organic components, the Zn eutectic solvent loses its organic component rather than decomposing (Wang et al., 2018). The DSC and TGA results together suggest that the ZE electrolyte is stable over a wide temperature range and should be superior to most aqueous and aprotic electrolytes used for ZIBs.

## Electrochemical Analysis

The electrochemical properties of the Zn eutectic electrolyte were investigated to ascertain its applicability in actual batteries. Initially, the electrochemical stability of the Zn eutectic mixture was investigated using a conventional three-electrode configuration comprising glassy C, Pt wire, and Ag wire



**FIGURE 8** | SEM images of Zn metal anode (A,B) 2 M ZnSO<sub>4</sub> electrolyte ZE electrolyte; (C,D) ZE electrolyte after 15 cycles at 1 mA cm<sup>-2</sup>.

immersed in a ZE electrolyte as the working, counter, and reference electrodes, respectively.

The cyclic voltammogram profile of the Zn eutectic combination (Figure 5) revealed that potentials less than  $-1.2$  V resulted in Zn<sup>2+</sup> electroplating, while those greater than  $1.05$  V vs. Ag wire resulted in EG breakdown. Therefore, the liquid has an impressive potential window of 2 V, which is limited by Zn electroplating at the cathodic end and gas evolution at the anodic end of the liquid. Similar to that of the choline chloride/2ZnCl<sub>2</sub> type I DES system, there is some indication of underpotential deposition at  $0.05$  V (Abbott et al., 2007b). Despite the Zn mole fraction and Zn species being significantly different in the ZE electrolyte (Type IV DES system), the potential window is nearly identical to those of their type I counterparts, which are widely used in electrochemical processes.

Another important aspect of Zn electrodes for ZIBs is the reversible plating/stripping of Zn metal anodes. The reversibility and stability of Zn in the ZE DES electrolyte were investigated using a Zn/Zn symmetric cell, where Zn electrodes were used as both positive and negative electrodes under galvanostatic conditions. Figures 6A,B show the results of cycling experiments in Zn|electrolyte|Zn cells at different current densities in the ZE electrolyte. During cycling, the polarization voltage was constrained by the maximum and minimum voltages at each current density.

Figure 6A shows that a relatively substantial initial overpotential is required to trigger the Zn plating/stripping reaction (shown by the red arrow), but the overpotential is reduced during consecutive cycles. Furthermore, the

maximum voltages did not increase during cycling, demonstrating that no passivation layer was formed on the Zn surface (Cui et al., 2021). The excellent performance of the Zn metal anode was further validated by long-term cycling at different current densities, as shown in Figure 7A. The symmetric cell operates steadily over 180 cycles (>300 h) at  $0.25$  mA h cm<sup>-2</sup>, indicating the high reversibility of the Zn anode. The polarization curve remained stable throughout the entire cycle process. On the other hand, a gradual increase in overpotential values was observed for symmetric cells (Zn/Zn) cycled at  $0.25$  mA h cm<sup>-2</sup> in the conventional aqueous ZnSO<sub>4</sub> electrolyte. Zn plating/stripping could only be cycled for 90 h at  $0.25$  mA h cm<sup>-2</sup> in the aqueous ZnSO<sub>4</sub> electrolyte (Figure 7B).

After 50 cycles at  $0.2$  mA h cm<sup>-2</sup>, we opened the Zn/Zn cell with both the aqueous ZnSO<sub>4</sub> and ZnSO<sub>4</sub>/EG/H<sub>2</sub>O electrolytes and found that the Zn foil possessed some black spots that would further grow and lead to cell death (Figure 7D). In contrast, the cell-cycled ZE electrolyte displayed no such black spots, indicating the high stability of the Zn anode in the ZE electrolyte. Benefiting from these features, the Zn/Zn symmetric cell showed excellent stability for 200 h at a high current density of  $1$  mA h cm<sup>-2</sup> with an overall overpotential value of less than 200 mV (Figure 7C).

Figure 8 shows SEM images of the typical morphology of Zn metal growths deposited in ZE DES and ZnSO<sub>4</sub> electrolyte at current density of  $1$  mA cm<sup>-2</sup> with a total charge of  $1$  mA h cm<sup>-2</sup>. Significant difference in morphologies is observed. After the 15th cycle, several large Zn protrusions

were found in the case of aqueous ZnSO<sub>4</sub>, but a smooth surface with relatively few large particles was observed in the case of Zn anode cycled in ZE electrolyte. As shown in high resolution SEM image, the Zn surface is mostly composed of small spherical particles (Inset of **Figure 8D**). The Zn symmetric cell further operates for 40 h at 2 mA cm<sup>-2</sup> with capacity of 2 mAh cm<sup>-2</sup> indicating good reversibility even at high current density (**Supplementary Figure S2**). **Supplementary Table S1** summarizes the performance comparison of ZE DES electrolyte with other DESs and EG-based electrolytes. The excellent cycling performance demonstrates the electrolyte's remarkable potential for ZIBs.

## CONCLUSION

A biocompatible, stable, and low-cost Zn-based deep eutectic solution was successfully fabricated in this study to stabilize the Zn metal anode in ZIBs with a larger stability window. Aqueous and DES media were combined in this electrolyte to allow for safe and reversible Zn plating and stripping, with a two-fold increase in the cycling life compared to that of traditional aqueous electrolytes. This electrolyte with improved Zn anode reversibility and cycling stability could lead to a higher energy density and more stable ZIBs than conventional aqueous ones.

## REFERENCES

- Abbott, A. P., Barron, J. C., and Ryder, K. S. (2013). Electrolytic Deposition of Zn Coatings from Ionic Liquids Based on Choline Chloride. *Int. J. Surf. Eng. Coat.* 87, 201–207. doi:10.1179/174591909X438857
- Abbott, A. P., Barron, J. C., Ryder, K. S., and Wilson, D. (2007a). Eutectic-Based Ionic Liquids with Metal-Containing Anions and Cations. *Chem. Eur. J.* 13, 6495–6501. doi:10.1002/CHEM.200601738
- Abbott, A. P., Harris, R. C., and Ryder, K. S. (2007b). Application of Hole Theory to Define Ionic Liquids by Their Transport Properties. *J. Phys. Chem. B* 111, 4910–4913. doi:10.1021/JP0671998
- Abbott, A. P., Ryder, K. S., and König, U. (2008). Electrofinishing of Metals Using Eutectic Based Ionic Liquids. *Trans. IMF* 86, 196–204. doi:10.1179/174591908X327590
- Cui, M., Fei, J., Mo, F., Lei, H., and Huang, Y. (2021). Ultra-High-Capacity and Dendrite-Free Zinc-Sulfur Conversion Batteries Based on a Low-Cost Deep Eutectic Solvent. *ACS Appl. Mater. Inter.* 13, 54981–54989. doi:10.1021/ACSAMI.1C15750
- Du, Y., Li, Y., Xu, B. B., Liu, T. X., Liu, X., Ma, F., et al. (2021). Electrolyte Salts and Additives Regulation Enables High Performance Aqueous Zinc Ion Batteries: A Mini Review. *Small*, 2104640. doi:10.1002/SMLL.202104640
- Hansen, E. J., and Liu, J. (2021). Materials and Structure Design for Solid-State Zinc-Ion Batteries: A Mini-Review. *Front. Energ. Res.* 8, 368. doi:10.3389/FENRG.2020.616665/BIBTEX
- Hong, S., Lian, H., Sun, X., Pan, D., Carranza, A., Pojman, J. A., et al. (2016). Zinc-based Deep Eutectic Solvent-Mediated Hydroxylation and Demethoxylation of Lignin for the Production of wood Adhesive. *RSC Adv.* 6, 89599–89608. doi:10.1039/C6RA18290A
- Hu, H., Ling, X., Tan, C., Lin, J., Han, X., and Hu, W. (2020). Preparation of Ni<sub>3</sub>Fe<sub>2</sub>@NC/CC Integrated Electrode and its Application in Zinc-Air Battery. *Front. Chem.* 8, 575288. doi:10.3389/FCHEM.2020.575288/BIBTEX
- Kalhor, P., Ghandi, K., Ashraf, H., and Yu, Z. (2021). The Structural Properties of a ZnCl<sub>2</sub>-Ethylene Glycol Binary System and the Peculiarities at the Eutectic

## DATA AVAILABILITY STATEMENT

The original contributions presented in the study are included in the article/**Supplementary Material**, further inquiries can be directed to the corresponding author.

## AUTHOR CONTRIBUTIONS

GT: Conceptualization, Methodology, Investigation, Software, Data curation, Writing-Original draft preparation. V-CH: Conceptualization, Methodology, Investigation, Software, Data curation. JM: Conceptualization, Supervision, Writing-Reviewing and Editing.

## FUNDING

This work was supported by the Post-Doctor Program (2018) of Incheon National University (INU), Incheon, South Korea.

## SUPPLEMENTARY MATERIAL

The Supplementary Material for this article can be found online at: <https://www.frontiersin.org/articles/10.3389/fchem.2021.825807/full#supplementary-material>

Composition. *Phys. Chem. Chem. Phys.* 23, 13136–13147. doi:10.1039/D1CP00573A

- Kao-ian, W., Nguyen, M. T., Yonezawa, T., Pornprasertsuk, R., Qin, J., Siwamogsatham, S., et al. (2021). Highly Stable Rechargeable Zinc-Ion Battery Using Dimethyl Sulfoxide Electrolyte. *Mater. Today Energ.* 21, 100738. doi:10.1016/J.MTENER.2021.100738
- Kaur, K., Juglan, K. C., Kumar, H., and Behal, I. (2018). Thermodynamic Interactions Study of Some Ethylene Glycols in Aqueous Aniline Solutions at Different Temperatures: An Acoustical and Volumetric Approach. *J. Chem. Eng. Data* 63, 3237–3251. doi:10.1021/acs.jced.8b00058
- Kazemiabnavi, S., Zhang, Z., Thornton, K., and Banerjee, S. (2016). Electrochemical Stability Window of Imidazolium-Based Ionic Liquids as Electrolytes for Lithium Batteries. *J. Phys. Chem. B* 120, 5691–5702. doi:10.1021/ACS.JPCB.6B03433
- Liu, C., Xie, X., Lu, B., Zhou, J., and Liang, S. (2021). Electrolyte Strategies toward Better Zinc-Ion Batteries. *ACS Energ. Lett.* 6, 1015–1033. doi:10.1021/ACSENERGYLETT.0C02684
- McDowell, S. A. C. (2003). Blue Shifting and Red Shifting Hydrogen Bonds: A Study of the HARF...N<sub>2</sub> and HARF...P<sub>2</sub> Complexes. *Phys. Chem. Chem. Phys.* 5, 808–811. doi:10.1039/B211014H
- Mo, F., Liang, G., Meng, Q., Liu, Z., Li, H., Fan, J., et al. (2019). A Flexible Rechargeable Aqueous Zinc Manganese-Dioxide Battery Working at -20 °C. *Energy Environ. Sci.* 12, 706–715. doi:10.1039/c8ee02892c
- Sanchora, P., Pandey, D. K., Rana, D., Materny, A., and Singh, D. K. (2019). Impact of Size and Electronegativity of Halide Anions on Hydrogen Bonds and Properties of 1-Ethyl-3-Methylimidazolium-Based Ionic Liquids. *J. Phys. Chem. A* 123, 4948–4963. doi:10.1021/acs.jpca.9b04116
- Sarjuna, K., and Ilangeswaran, D. (2020). Preparation of Some Zinc Chloride Based Deep Eutectic Solvents and Their Characterization. *Mater. Today Proc.* 33, 2767–2770. doi:10.1016/j.matpr.2020.02.080
- Sun, C., Wu, C., Gu, X., Wang, C., and Wang, Q. (2021). Interface Engineering via Ti<sub>3</sub>C<sub>2</sub>T<sub>x</sub> MXene Electrolyte Additive toward Dendrite-free Zinc Deposition. *Nano-Micro Lett.* 13, 1–13. doi:10.1007/S40820-021-00612-8

- Thorat, G. M., Jadhav, H. S., Roy, A., Chung, W.-J., and Seo, J. G. (2018). Dual Role of Deep Eutectic Solvent as a Solvent and Template for the Synthesis of Octahedral Cobalt Vanadate for an Oxygen Evolution Reaction. *ACS Sustain. Chem. Eng.* 6, 16255–16266. doi:10.1021/acsschemeng.8b03119
- Tran, P. H., and Thi Hang, A.-H. (2018). Deep Eutectic Solvent-Catalyzed Arylation of Benzoxazoles with Aromatic Aldehydes. *RSC Adv.* 8, 11127–11133. doi:10.1039/C8RA01094C
- Wang, N., Yang, G., Gan, Y., Wan, H., Chen, X., Wang, C., et al. (2020a). Contribution of Cation Addition to MnO<sub>2</sub> Nanosheets on Stable Co<sub>3</sub>O<sub>4</sub> Nanowires for Aqueous Zinc-Ion Battery. *Front. Chem.* 8, 793. doi:10.3389/fchem.2020.00793
- Wang, N., Yang, Y., Qiu, X., Dong, X., Wang, Y., and Xia, Y. (2020b). Stabilized Rechargeable Aqueous Zinc Batteries Using Ethylene Glycol as Water Blocker. *ChemSusChem* 13, 5556–5564. doi:10.1002/cssc.202001750
- Wang, Y., Niu, Z., Zheng, Q., Zhang, C., Ye, J., Dai, G., et al. (2018). Zn-Based Eutectic Mixture as Anolyte for Hybrid Redox Flow Batteries. *Sci. Rep.* 8 (1), 1–8. doi:10.1038/s41598-018-24059-x
- Wilcox, R. J., Losey, B. P., Folmer, J. C. W., Martin, J. D., Zeller, M., and Sommer, R. (2015). Crystalline and Liquid Structure of Zinc Chloride Trihydrate: A Unique Ionic Liquid. *Inorg. Chem.* 54, 1109–1119. doi:10.1021/IC5024532/SUPPL\_FILE/IC5024532\_SI\_002.CIF
- Wu, H.-Y., Gu, X., Huang, P., Sun, C., Hu, H., Zhong, Y., et al. (2021a). Polyoxometalate Driven Dendrite-free Zinc Electrodes with Synergistic Effects of Cation and Anion Cluster Regulation. *J. Mater. Chem. A.* 9, 7025–7033. doi:10.1039/D1TA00256B
- Wu, Y., Song, T.-Y., Chen, L.-N., and Chen, -Na. (2021b). A Review on Recent Developments of Vanadium-Based Cathode for Rechargeable Zinc-Ion Batteries. *Tungsten* 3 (3), 289–304. doi:10.1007/S42864-021-00091-9
- Xu, C.-X., and Jiang, J.-J. (2021). Electrolytes Speed up Development of Zinc Batteries. *Rare Met.* 40, 749–751. doi:10.1007/S12598-020-01628-6/FIGURES/2
- Zhang, C., Holoubek, J., Wu, X., Daniyar, A., Zhu, L., Chen, C., et al. (2018a). A ZnCl<sub>2</sub> Water-in-Salt Electrolyte for a Reversible Zn Metal Anode. *Chem. Commun.* 54, 14097–14099. doi:10.1039/C8CC07730D
- Zhang, N., Dong, Y., Jia, M., Bian, X., Wang, Y., Qiu, M., et al. (2018b). Rechargeable Aqueous Zn-V<sub>2</sub>O<sub>5</sub> Battery with High Energy Density and Long Cycle Life. *ACS Energ. Lett.* 3, 1366–1372. doi:10.1021/acenergylett.8b00565
- Zhang, T., Tang, Y., Guo, S., Cao, X., Pan, A., Fang, G., et al. (2020). Fundamentals and Perspectives in Developing Zinc-Ion Battery Electrolytes: A Comprehensive Review. *Energ. Environ. Sci.* 13, 4625–4665. doi:10.1039/D0EE02620D
- Zhao, J., Zhang, J., Yang, W., Chen, B., Zhao, Z., Qiu, H., et al. (2019). “Water-in-deep Eutectic Solvent” Electrolytes Enable Zinc Metal Anodes for Rechargeable Aqueous Batteries. *Nano Energy* 57, 625–634. doi:10.1016/J.NANOEN.2018.12.086
- Zhu, M., Wang, X., Tang, H., Wang, J., Hao, Q., Liu, L., et al. (2019). Antifreezing Hydrogel with High Zinc Reversibility for Flexible and Durable Aqueous Batteries by Cooperative Hydrated Cations. *Adv. Funct. Mater.* 30, 1907218. doi:10.1002/adfm.201907218
- Zhu, Q.-N., Wang, Z.-Y., Wang, J.-W., Liu, X.-Y., Yang, D., Cheng, L.-W., et al. (2021). Challenges and Strategies for Ultrafast Aqueous Zinc-Ion Batteries. *Rare Met.* 40, 309–328. doi:10.1007/S12598-020-01588-X/FIGURES/9

**Conflict of Interest:** The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

**Publisher’s Note:** All claims expressed in this article are solely those of the authors and do not necessarily represent those of their affiliated organizations, or those of the publisher, the editors and the reviewers. Any product that may be evaluated in this article, or claim that may be made by its manufacturer, is not guaranteed or endorsed by the publisher.

Copyright © 2022 Thorat, Ho and Mun. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) and the copyright owner(s) are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.