



Commentary: *Ex Situ* Aqueous Mineral Carbonation

Greeshma Gadikota*

Department of Civil and Environmental Engineering, Princeton University, Princeton, NJ, USA

Keywords: mineral carbonation, carbon mineralization, CO₂ conversion, utilization and storage, magnesium and calcium silicates, magnesium and calcium carbonates, alkaline industrial wastes

A commentary on

Ex Situ Aqueous Mineral Carbonation

by Gerdemann, S. J., O'Connor, W. K., Dahlin, D. C., Penner, L. R., and Rush, H. (2007). *Environ. Sci. Technol.* **41**, 2587–2593. doi: 10.1021/es0619253

CO₂ conversion to calcium and magnesium carbonates has garnered considerable attention since it is a thermodynamically downhill pathway to safely and permanently sequester large quantities of CO₂. This seminal work performed at The National Energy Technology Laboratory in Albany (NETL-Albany) reports the conversion of calcium- and magnesium-bearing silicate minerals, such as olivine [(Mg, Fe)₂SiO₄], wollastonite (CaSiO₃), and serpentine [Mg₃Si₂O₅(OH)₄], as they are reacted with CO₂ in an aqueous environment to form magnesium or calcium carbonates. This paper discusses various pretreatment methods of the starting materials, such as grinding or heat treatment of hydroxylated Mg silicates, to enhance the reaction kinetics. The effects of various chemical additives (e.g., NaCl and NaHCO₃), and reaction parameters, such as temperature, pressure, and reaction time, on the conversion are investigated. Feasibility assessments and energy and economic analyses of the direct carbonation of calcium- and magnesium-bearing minerals are presented.

The key contributions of this study are the identification of the optimal conditions for the carbonation of olivine (185°C, P_{CO₂} = 150 atm, 1.0M·NaCl + 0.64M·NaHCO₃), wollastonite (100°C, P_{CO₂} = 40 atm, distilled water), and heat-treated serpentine (155°C, P_{CO₂} = 150 atm, 1.0M·NaCl + 0.64M·NaHCO₃). High extents of carbonation of 49.5, 81.8, and 73.5% of olivine, wollastonite, and heat-treated serpentine, respectively, achieved within an hour of reacting with CO₂ in an aqueous environment are reported. The identification of the optimal reaction conditions to achieve the rapid conversion of calcium- and magnesium-bearing silicate minerals to carbonates has spurred a significant global scientific interest in mineral carbonation as a promising technology for CO₂ conversion and storage with the potential reuse of carbonates.

In particular, this work has found unique relevance for *ex situ* and *in situ* carbon mineralization. In *ex situ* mineral carbonation, CO₂ is converted to carbonates in engineered processes where there is considerable control over the reaction conditions. In *in situ* mineral carbonation, CO₂ is injected into geological formations containing calcium- and magnesium-bearing minerals and rocks with the aim toward natural carbon mineralization over time. Predicting the fate of CO₂ injected into geological formations containing these rocks and minerals and developing chemical processes for converting CO₂ to carbonates require a fundamental understanding of the kinetics of mineral carbonation and the corresponding morphological changes in materials. Thus, more recent studies have focused on understanding the carbon mineralization behavior *via* direct carbonation (Bonfils et al., 2012; Gadikota et al., 2014a; Eikeland et al., 2015) and indirect carbonation, which involves the dissolution of minerals (Park et al., 2003; Park and Fan, 2004; Hänchen et al., 2006; Prigiobbe et al., 2009; Gadikota et al., 2014b), formation of carbonates (Ferrini et al., 2009; Saldi et al., 2009, 2012; Cheng and Li, 2010; Bénézech et al., 2011; Zhao et al., 2013; Fricker and Park, 2014; Swanson

OPEN ACCESS

Edited by:

Peter Styring,
The University of Sheffield, UK

Reviewed by:

Ron Zevenhoven,
Åbo Akademi University, Finland

*Correspondence:

Greeshma Gadikota
gadikota@princeton.edu

Specialty section:

This article was submitted to Carbon
Capture, Storage, and Utilization,
a section of the journal
Frontiers in Energy Research

Received: 18 March 2016

Accepted: 12 May 2016

Published: 26 May 2016

Citation:

Gadikota G (2016) Commentary: *Ex Situ Aqueous Mineral Carbonation*.
Front. Energy Res. 4:21.
doi: 10.3389/fenrg.2016.00021

et al., 2014), and the corresponding morphological changes in materials (Hövelmann et al., 2012; Olsson et al., 2012; Gadikota et al., 2014a). The effects of sodium and ammonium salts and Si-, Mg-, and Ca-targeting chelating agents on enhancing mineral carbonation behavior has been investigated (Bonfils et al., 2012; Highfield et al., 2012; Declercq et al., 2013; Zhao et al., 2013; Gadikota et al., 2014a,b; Ghoorah et al., 2014).

These studies have formed the basis for understanding CO₂ interactions with calcium and magnesium silicates that extend beyond the laboratory to the demonstration scale (Reddy et al., 2010; Kelly et al., 2011; Zevenhoven et al., 2011; Hitch and Dipple, 2012; Brent, 2015) and toward geological carbon storage (Kelemen and Matter, 2008; Matter and Kelemen, 2009; Schaefer and McGrail, 2009; Gislason et al., 2010; Rosenbauer et al., 2012). The studies performed at NETL-Albany have also been extensively cited in studies for the accelerated carbonation of industrial alkaline wastes [Pan et al. (2012), Gadikota and Park (2014), Sanna et al. (2012), and references contained therein]. These materials are often fine, highly reactive, and have a high Ca and Mg content. Examples of these materials include coal fly ash, steel and stainless steel slags, cement and lime kiln dusts, and red mud. However, the availability of industrial alkaline wastes is much smaller compared to calcium- and magnesium-bearing silicate minerals. The global CO₂ storage potential of industrial alkaline wastes is about 200–300 Mt of CO₂ per year, while calcium- and magnesium-bearing silicates can store carbon to the order of thousands of Gt (Sanna et al., 2012). Regardless, the integration of carbon mineralization technologies with these carbon-intensive industries reduces the CO₂ footprint, the alkalinity of the wastes, and could lead to the potential reuse of the carbonated materials as building, construction, or filler materials. Further development of carbon mineralization technologies requires a fundamental understanding of the formation of mass transfer limiting layers containing Si and Fe (Béarat et al., 2006; King et al., 2010; Daval et al., 2011; Saldi et al., 2013, 2015; Sissmann et al., 2013; Harrison et al., 2015), linkages between the morphology with the chemistry (Hövelmann et al., 2012; Olsson et al., 2012; Gadikota et al., 2014a; Eikeland et al., 2015), and the impact of impurities in the gas streams (e.g., SO₂) on the conversion of CO₂ to carbonates (Liu et al., 2010; Zevenhoven et al., 2014). While

these findings are in the context of *ex situ* mineral carbonation, they are of relevance to *in situ* conversion of CO₂ to carbonates.

When CO₂ is directly injected into geological reservoirs with calcium- and magnesium-bearing silicates, carbonate formation is aided by the geothermal gradient, which provides reaction temperatures in excess of 80°C, P_{CO₂} ~ 80–150 bar available post-combustion and compression, and the presence of ground water. These conditions are analogous to the reaction conditions identified in this study. Of particular interest are the Oman peridotite (olivine-rich rock) (Kelemen and Matter, 2008; Matter and Kelemen, 2009) and the basalts in Iceland and Columbia River in the United States (Matter et al., 2009; McGrail et al., 2011). The chemomechanical effects due to extensive carbonate growth may induce microfractures, which in turn impact the permeability, fluid flow, and further reactivity of the rock (Kelemen et al., 2013). Regardless, the permanent *in situ* conversion of CO₂ to carbonates reduces the need to monitor mobile CO₂ over time.

While the experimental methodologies developed by the researchers at NETL-Albany have laid the foundation for a number of studies in this field, considerable uncertainties in the energy requirements for mineral carbonation exist. These uncertainties are attributed to some key parameters, such as the availability and cost of the feedstock, preprocessing of the materials, such as crushing and grinding, the conversion routes, and the use of heat vs. electricity. Regardless, the work performed at NETL-Albany has highlighted the need for a multi-scale understanding of the kinetics, mass transfer behaviors, competing reactions, and microstructural and chemical changes in heterogeneous materials, when reacted with CO₂. These insights can be used to tune the reactivity and morphology of the carbonated end-materials. Ultimately, a fundamental understanding of CO₂-reaction fluid-mineral/rock interactions is essential for developing large-scale chemical processes for converting CO₂ to carbonates, and for predicting the fate of CO₂ injected into geological formations containing calcium and magnesium silicate minerals and rocks.

AUTHOR CONTRIBUTIONS

The author confirms being the sole contributor of this work and approved it for publication.

REFERENCES

- Béarat, H., McKelvy, M. J., Chizmeshya, D., Gormley, A. V., Nunez, R., Carpenter, R. W., et al. (2006). Carbon sequestration via aqueous olivine mineral carbonation: role of passivating layer formation. *Environ. Sci. Technol.* 40, 4802–4808. doi:10.1021/es0523340
- Bénézech, P., Saldi, G. D., Dandurand, J.-L., and Schott, J. (2011). Experimental determination of the solubility product of magnesite at 50 to 200°C. *Chem. Geol.* 286, 21–31. doi:10.1016/j.chemgeo.2011.04.016
- Bonfils, B., Julcour-Lebigue, C., Guyot, F., Bodéan, F., Chiquet, P., and Bourgeois, F. (2012). Comprehensive analysis of direct aqueous mineral carbonation using dissolution enhancing organic additives. *Int. J. Greenhouse Gas Control* 9, 334–346. doi:10.1016/j.jggc.2012.05.009
- Brent, G. F. (2015). “Mineral carbonation of serpentinite: from the laboratory to pilot scale – the MCi project,” in *Accelerated Carbonation for Environmental and Material Engineering* (New York City).
- Cheng, W., and Li, Z. (2010). Controlled supersaturation precipitation of hydro-magnesite for the MgCl₂-Na₂CO₃ system at elevated temperatures: chemical modeling and experiment. *Ind. Eng. Chem. Res.* 49, 1964–1974. doi:10.1021/ie9015073
- Daval, D., Sissmann, O., Menguy, N., Saldi, G. D., Guyot, F., Martinez, I., et al. (2011). Influence of amorphous silica layer formation on the dissolution rate of olivine at 90°C and elevated pCO₂. *Chem. Geol.* 284, 193–209. doi:10.1016/j.chemgeo.2011.02.021
- Declercq, J., Bosc, O., and Oelkers, E. H. (2013). Do organic ligands affect forsterite dissolution rates? *Appl. Geochem.* 39, 69–77. doi:10.1016/j.apgeochem.2013.09.020
- Eikeland, E., Blichfeld, A. B., Tyrsted, C., Jensen, A., and Iversen, B. B. (2015). Optimized carbonation of magnesium silicate mineral for CO₂ storage. *ACS Appl. Mater. Interfaces* 7, 5258–5264. doi:10.1021/am508432w
- Ferrini, V., De Vito, C., and Mignardi, S. (2009). Synthesis of nesquehonite by reaction of gaseous CO₂ with Mg chloride solution: its potential role in the sequestration of carbon dioxide. *J. Hazard. Mater.* 168, 832–837. doi:10.1016/j.jhazmat.2009.02.103
- Fricke, K. J., and Park, A. H. A. (2014). Investigation of the different carbonate phases and their formation kinetics during Mg(OH)₂ slurry carbonation. *Ind. Eng. Chem. Res.* 53, 18170–18179. doi:10.1021/ie503131s

- Gadikota, G., Matter, J., Kelemen, P. B., and Park, A. H. A. (2014a). Chemical and morphological changes during olivine carbonation for CO₂ storage in the presence of NaCl and NaHCO₃. *Phys. Chem. Chem. Phys.* 16, 4679–4693. doi:10.1039/c3cp54903h
- Gadikota, G., Swanson, E. J., Zhao, H., and Park, A. H. A. (2014b). Experimental design and data analysis for accurate estimation of reaction kinetics and conversion for carbon mineralization. *Ind. Eng. Chem. Res.* 53, 6664–6676. doi:10.1021/ie500393h
- Gadikota, G., and Park, A.-H. A. (2014). “Accelerated carbonation of Ca- and Mg-bearing minerals and industrial wastes using CO₂,” in *Carbon Dioxide Utilization: Closing the Carbon Cycle*, 1st Edn, eds P. Styring and A. Quadrelli (Elsevier), 115–134.
- Ghoorah, M., Dlugogorski, B. Z., Balucan, R. D., and Kennedy, E. M. (2014). Selection of acid for weak acid processing of wollastonite for mineralisation of CO₂. *Fuel* 122, 277–286. doi:10.1016/j.fuel.2014.01.015
- Gislason, S. R., Wolff-Boenisch, D., Stefansson, A., Oelkers, E. H., Gunnlaugsson, E., Sigurdardottir, H., et al. (2010). Mineral sequestration of carbon dioxide in basalt: a pre-injection overview of the CarbFix project. *Int. J. Greenhouse Gas Control* 4, 537–545. doi:10.1016/j.ijggc.2009.11.013
- Hänchen, M., Prigiobbe, V., Storti, G., Seward, T. M., and Mazzotti, M. (2006). Dissolution kinetics of forsteritic olivine at 90–150°C including effects of the presence of CO₂. *Geochim. Cosmochim. Acta* 70, 4403–4416. doi:10.1016/j.gca.2006.06.1560
- Harrison, A. L., Dipple, G. M., Power, I. M., and Mayer, K. U. (2015). Influence of surface passivation and water content on mineral reactions in unsaturated porous media: implications for brucite carbonation and CO₂ sequestration. *Geochim. Cosmochim. Acta* 148, 477–495. doi:10.1016/j.gca.2014.10.020
- Highfield, J., Lim, H., Fagerlund, J., and Zevenhoven, R. (2012). Activation of serpentine for CO₂ mineralization by flux extraction of soluble magnesium salts using ammonium sulfate. *RSC Adv.* 2, 6535–6541. doi:10.1039/c2ra01347a
- Hitch, M., and Dipple, G. M. (2012). Economic feasibility and sensitivity analysis of integrating industrial-scale mineral carbonation into mining operations. *Miner. Eng.* 39, 268–275. doi:10.1016/j.mineng.2012.07.007
- Hövelmann, J., Austrheim, H., and Jamtveit, B. (2012). Microstructure and porosity evolution during experimental carbonation of a natural peridotite. *Chem. Geol.* 334, 254–265. doi:10.1016/j.chemgeo.2012.10.025
- Kelemen, P. B., and Matter, J. M. (2008). In situ carbonation of peridotite for CO₂ storage. *Proc. Natl. Acad. Sci. U.S.A.* 105, 17295–17300. doi:10.1073/pnas.0805794105
- Kelemen, P. B., Savage, H., and Hirth, G. (2013). “Reaction-driven cracking during mineral hydration, carbonation and oxidation,” in *Poromechanics V: Proceedings of the Fifth Biot Conference on Poromechanics* (Reston, VA: American Society of Civil Engineers), 823–826.
- Kelly, K. E., Silcox, G. D., Sarofim, A. F., and Pershing, D. W. (2011). An evaluation of ex situ, industrial-scale, aqueous CO₂ mineralization. *Int. J. Greenhouse Gas Control* 5, 1587–1595. doi:10.1016/j.ijggc.2011.09.005
- King, H. E., Plümper, O., and Putnis, A. (2010). Effect of secondary phase formation on the carbonation of olivine. *Environ. Sci. Technol.* 44, 6503–6509. doi:10.1021/es9038193
- Liu, C. F., Shih, S. M., and Huang, T. B. (2010). Effect of SO₂ on the reaction of calcium hydroxide with CO₂ at low temperatures. *Ind. Eng. Chem. Res.* 49, 9052–9057. doi:10.1021/ie100924z
- Matter, J. M., Broecker, W. S., Stute, M., Gislason, S. R., Oelkers, E. H., Stefansson, A., et al. (2009). Permanent carbon dioxide storage into basalt: the CarbFix Pilot Project, Iceland. *Energy Proc.* 1, 3641–3646. doi:10.1016/j.egypro.2009.02.160
- Matter, J. M., and Kelemen, P. B. (2009). Permanent storage of carbon dioxide in geological reservoirs by mineral carbonation. *Nat. Geosci.* 2, 837–841. doi:10.1038/ngeo683
- McGrail, B. P., Spane, F. A., Sullivan, E. C., Bacon, D. H., and Hund, G. (2011). The Wallula basalt sequestration pilot project. *Energy Proc.* 4, 5653–5660. doi:10.1016/j.egypro.2011.02.557
- Olsson, J., Bovet, N., Makovicky, E., Bechgaard, K., Balogh, Z., and Stipp, S. L. S. (2012). Olivine reactivity with CO₂ and H₂O on a microscale: implications for carbon sequestration. *Geochim. Cosmochim. Acta* 77, 86–97. doi:10.1016/j.gca.2011.11.001
- Pan, S. Y., Chang, E. E., and Chiang, P. C. (2012). CO₂ capture by accelerated carbonation of alkaline wastes: a review on its principles and applications. *Aerosol Air Qual. Res.* 12, 770–791. doi:10.4209/aaqr.2012.06.0149
- Park, A. H. A., and Fan, L.-S. (2004). CO₂ mineral sequestration: physically activated dissolution of serpentine and pH swing process. *Chem. Eng. Sci.* 59, 5241–5247. doi:10.1016/j.ces.2004.09.008
- Park, A. H. A., Jadhav, R., and Fan, L.-S. (2003). CO₂ mineral sequestration?: chemically enhanced aqueous carbonation of serpentine. *Can. J. Chem. Eng.* 81, 885–890. doi:10.1002/cjce.5450810373
- Prigiobbe, V., Costa, G., Baciocchi, R., Hänchen, M., and Mazzotti, M. (2009). The effect of CO₂ and salinity on olivine dissolution kinetics at 120°C. *Chem. Eng. Sci.* 64, 3510–3515. doi:10.1016/j.ces.2009.04.035
- Reddy, K. J., Weber, H., Bhattacharyya, P., Argyle, M., Taylor, D., Christensen, M., et al. (2010). Instantaneous capture and mineralization of flue gas carbon dioxide: pilot scale study. *Nat. Precedings*. doi:10.1038/npre.2010.5404.1
- Rosenbauer, R. J., Thomas, B., Bischoff, J. L., and Palandri, J. (2012). Carbon sequestration via reaction with basaltic rocks: geochemical modeling and experimental results. *Geochim. Cosmochim. Acta* 89, 116–133. doi:10.1016/j.gca.2012.04.042
- Saldi, G. D., Daval, D., Guo, H., Guyot, F., Bernard, S., Le Guillou, C., et al. (2015). Mineralogical evolution of Fe-Si-rich layers at the olivine-water interface during carbonation reactions. *Am. Mineral.* 100, 2655–2669. doi:10.2138/am-2015-5340
- Saldi, G. D., Daval, D., Morvan, G., and Knauss, K. G. (2013). The role of Fe and redox conditions in olivine carbonation rates: an experimental study of the rate limiting reactions at 90 and 150°C in open and closed systems. *Geochim. Cosmochim. Acta* 118, 157–183. doi:10.1016/j.gca.2013.04.029
- Saldi, G. D., Jordan, G., Schott, J., and Oelkers, E. H. (2009). Magnesite growth rates as a function of temperature and saturation state. *Geochim. Cosmochim. Acta* 73, 5646–5657. doi:10.1016/j.gca.2009.06.035
- Saldi, G. D., Schott, J., Pokrovsky, O. S., Gautier, Q., and Oelkers, E. H. (2012). An experimental study of magnesite precipitation rates at neutral to alkaline conditions and 100–200°C as a function of pH, aqueous solution composition and chemical affinity. *Geochim. Cosmochim. Acta* 83, 93–109. doi:10.1016/j.gca.2011.12.005
- Sanna, A., Hall, M. R., and Maroto-Valer, M. (2012). Post-processing pathways in carbon capture and storage by mineral carbonation (CCSM) towards the introduction of carbon neutral materials. *Energy Environ. Sci.* 5, 7781. doi:10.1039/c2ee03455g
- Schaefer, H. T., and McGrail, B. P. (2009). Dissolution of Columbia River Basalt under mildly acidic conditions as a function of temperature: experimental results relevant to the geological sequestration of carbon dioxide. *Appl. Geochem.* 24, 980–987. doi:10.1016/j.apgeochem.2009.02.025
- Sissmann, O., Daval, D., Brunet, F., Guyot, F., Verlaquet, A., Pinquier, Y., et al. (2013). The deleterious effect of secondary phases on olivine carbonation yield: insight from time-resolved aqueous-fluid sampling and FIB-TEM characterization. *Chem. Geol.* 357, 186–202. doi:10.1016/j.chemgeo.2013.08.031
- Swanson, E. J., Fricker, K. J., Sun, M., and Park, A.-H. A. (2014). Directed precipitation of hydrated and anhydrous magnesium carbonates for carbon storage. *Phys. Chem. Chem. Phys.* 16, 23440–23450. doi:10.1039/C4CP03491K
- Zevenhoven, R., Fagerlund, J., Björklöf, T., Mäkelä, M., and Eklund, O. (2014). Carbon dioxide mineralisation and integration with flue gas desulphurisation applied to a modern coal-fired power plant. *J. Energy Power Eng.* 8, 431–447.
- Zevenhoven, R., Fagerlund, J., and Songok, J. K. (2011). CO₂ mineral sequestration: developments toward large-scale application. *Greenhouse Gases Sci. Technol.* 1, 48–57. doi:10.1002/ghg3.7
- Zhao, H., Park, Y., Lee, D. H., and Park, A. H. A. (2013). Tuning the dissolution kinetics of wollastonite via chelating agents for CO₂ sequestration with integrated synthesis of precipitated calcium carbonates. *Phys. Chem. Chem. Phys.* 15, 15185–15192. doi:10.1039/c3cp52459k

Conflict of Interest Statement: The author declares that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

Copyright © 2016 Gadikota. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) or licensor are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.